

FORMULA RECORD 6

CONTROL LAB Cleveland T. S.

DATE 10-28-53

REX. NO. 472

NAME S W P Mildew Resisting White

CARD NO. 10

POUNDS	GALLONS	NEW MAT'L	OLD MAT'L
300	12.6	6232	312
75	2.3	6603	2030
75	2.3	6600	1103
150	9.3	6810	112
60	1.1	6822	18
6	0.7	(1960)	(5091)
17	6	(2702)	(798)
100	13	(1521)	(2)
210	28	(2536)	(2536)*
121	12 3/4	(1071)	(1071)
6	3/4	(902)	(1230)
2	1 1/4	(912)	(1231)
87	13 1/4	(151)	(5027)
18	1 1/4	(2539)	(2539)
9	3/4	(115)	(348)

CUSTOMER Sherwin-Williams Co.
MFG. INSTR. Up to 2 gals (348) is
permitted to adjust viscosity.

Label Caution H2
WT./GAL T 15.03 visc 28² 2 sec. @ 75° F
GRIND 2-3H visen #3 SW cup
OUTPUT 100 BLEED
MFG. LOSS 2% DEPT. PKG.
STOR. LOSS MILL. Roller LINING
SOLIDS RATE/HR LABEL ANALYSIS C
PARALLELS CARD NO. ABOVE 100° F LABEL NO RED X RED
No Parallel ROYALTY YES ☐ NO ☐ X ☐ W ☐
REASON FOR REVISION To replace (141) &
(348) with (5027).

FORMULATOR *W. B. Thompson* SUPT. *876*

0007-SWP-062088

TO PATCH Standard		REX NO. 172 H. B. 6-18-33
APPLICATION: SURFACE Wood Ext.		CARD NO. 9
NO. COATS one		DATE 6-12-53
UNDERCOATER USED		DATE 6-18-53
METHOD 1 Brush		SLIP NO.
REDUCTION: AMOUNT	REDUCER USED	AMOUNT
METHOD 2		
REDUCTION: AMOUNT	REDUCER USED	
DRYING TIME: TOUCH 6-8hrs	RECOAT 2-4days	FACTORY
HARD	SAND	FORMULA
TACK FREE	RUB	SPEC. CARD
BAKING TIME AND TEMP.		EXEC. COST DEPT.
GLOSS Oil	FILM Elastic	CLEVELAND
SPECIAL TESTS		KENSINGTON
		PAINT RESEARCH
		KENS. TECH. SERV.
		KENS. LACQUER
		NEWARK
		OAKLAND
		M. SENOUR
		DETROIT
		LOS ANGELES
		DALLAS
		DAYTON
		GIBBSBORO
		EXEC. MFG.
		CUBA
		MONTREAL
		BUENOS AIRES
		BRAZIL
		REC. ADM.
		MEXICO

Phil-Ven

47	8	(198)	W. LOSS	200	WISC. ON #3 CUP	100	PKG.
100	13	(2)	GRIND	100	BLEED	100	LINING
146	18 1/4	(25 ALL)	OUTPUT	100	WISC. LOSS	200	LABEL ANALYSIS C
121	12 3/4	(107)	WISC. LOSS	200	FLASH PT.	100	LABEL NO REDD: REDD
6	3/4	(1230)	STOR. LOSS	100	ROYALTY: YES ☐ NO ☒ W D	100	TO SHOW (25 ALL) IN
2	1/4	(1231)	SOLDS	100	REASON FOR REVISION	100	Place of (2538).
124	19	(348)	PARALLELS	100	No Paralleled	100	
27	1	(141)		100		100	

FORMULATED BY P. J. Thompson SUPPLY 8776

TO MATCH Standard
 APPLICATION: SURFACE Wood-Ext
 NO. COATS one

UNDERCOATER USED

METHOD 1 Brush

REDUCTION: AMOUNT

REDUCER USED

METHOD 2

REDUCTION: AMOUNT

REDUCER USED

DRYING TIME: TOUCH 9hrs RECOAT 2-1/2 days STENCIL

HARD

SAND

HANDLE

TACK FREE

RUB

WRAP

BAKING TIME AND TEMP.

GLOSS Oil

FILM

Elastic

SPECIAL TESTS

REX. NO. 472 H.B. 3-23-53
 CARD NO. 8 ATTA Travel Sales
 DATE 3-12-53 Power Test

DATE	SLIP NO.	AMOUNT
<u>Quality Control</u>	<u>8-23-53</u>	
<u>Exp. H.</u>		
<u>Power</u>		
<u>Blowdown</u>		
<u>Scrub</u>		
FACTORY	FORMULA	SPEC. CARD
EXEC. COST DEPT.	<u>"</u>	
CLEVELAND	<u>"</u>	
KENSINGTON	<u>"</u>	<u>3-23-53</u>
PAINT RESEARCH	<u>"</u>	
KENS. TECH. SERV.	<u>"</u>	
KENS. LACQUER	<u>"</u>	
NEWARK	<u>"</u>	<u>4-23-53</u>
OAKLAND	<u>"</u>	
M. SENOUR	<u>"</u>	<u>3-23-53</u>
DETROIT	<u>"</u>	
LOS ANGELES	<u>"</u>	
DALLAS	<u>"</u>	
DAYTON	<u>"</u>	
GIBBSBORO	<u>"</u>	
EXEC. MFG.	<u>"</u>	
CUBA	<u>"</u>	
MONTREAL	<u>"</u>	
BUENOS AIRES	<u>"</u>	
BRAZIL	<u>"</u>	
RES ADM	<u>"</u>	
MEXICO	<u>"</u>	

0007-SWP-062093

FORMULA RECORD 6

CONTROL LAB Cleveland T.S.

DATE 10-5-52

REV. NO. 472

NAME S W P White Mildew Resisting

CARD NO. 8

POUNDS	GALLONS	MATERIAL NO.	CUSTOMER
300	12.6	6230 or 312	Sherwin-Williams Co.
75	2.3	2030	TO MATCH Standard
75	2.3	1403	
450	9.3	412	REASON FOR REVISION <u>to replace 20 dry</u>
60	1.1	18	<u>with 6230 dry.</u>
6	.7	(5094)	
47	6	(798)	VISCOSITY <u>30-38"</u> @ <u>75° F</u> AT _____ HRS. AFTER GRIND
100	13	(2)	VISCOSITY on #3 cup AT _____ HRS. AFTER GRIND
210	28	(2538)	% SOLIDS (RUN) _____ ROYALTY: YES ☐ ; NO ☐ ; X ☐ ; W ☐
121	12 3/4	(1071)	WT./GAL <u>15.04</u> LABEL ANALYSIS CHECKED <u>C</u>
6	3/4	(4230)	BAUME _____ LABEL: NO. RED ☒ ; RED ☐
2	1/4	(4231)	STD. OF FINENESS <u>2-3</u> NEW STD. SAMPLE REQUIRED
60	9 1/4	(348)	NORMAL OUTPUT <u>100</u> DATE REC'D _____
27	4	(141)	EST. MFG. LOSS <u>2%</u> MILL <u>Roller</u> BLEED? _____
			DEPARTMENT _____ LBS. OR GALS. PER HOUR _____
			PACKAGE _____ APPROVED <u>[Signature]</u>
			PARALLEL NO.'S _____ FORMULATOR <u>[Signature]</u>
			<u>No Parallel</u> SUPT. <u>S. F. L.</u>

0007-SWP-062094

MANUFACTURING INSTRUCTIONS:

Rex 472

APPLICATION: SURFACE Wood Ext.NO. COATS oneUNDERCOATER USED Rx 451METHOD 1 BrushREDUCTION: AMOUNT REDUCER USED METHOD 2 REDUCTION: AMOUNT REDUCER USED DRYING TIME: TOUCH 6-8hrs RECOAT 2-4days STENCIL HARD SAND HANDLE TACK FREE RUB WRAP BAKING TIME AND TEMP. GLOSS Oil FILM ElasticSPECIAL TESTS

DATE	SLIP NO.	AMOUNT
<i>Wm. B. Brown</i>	<i>10-14-52</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
<i>Wm. B. Brown</i>	<i>11</i>	<i>11</i>
FACTORY	FORMULA	SPEC. CARD
EXEC. COST DEPT.	<i>11</i>	
CLEVELAND A	<i>11</i>	
KENSINGTON C	<i>11</i>	<i>10-14-52</i>
ALLIED RESEARCH	<i>11</i>	
KENS. TECH. SERV.	<i>11</i>	
KENS. LACQUER		
NEWARK N	<i>11</i>	<i>10-14-52</i>
OAKLAND O	<i>11</i>	<i>10-14-52</i>
M. SENOUR M	<i>11</i>	<i>10-14-52</i>
DETROIT D	<i>11</i>	
LOS ANGELES P	<i>11</i>	
DALLAS T	<i>11</i>	
DAYTON I	<i>11</i>	
GIBBSERO F	<i>11</i>	
EXEC. MFG	<i>11</i>	
CUBA H	<i>11</i>	
MONTREAL G	<i>11</i>	
BUENOS AIRES Z	<i>11</i>	
BRAZIL S	<i>11</i>	
RES ADM	<i>11</i>	
MEXICO	<i>11</i>	

0007-SWP-062095

FORMULA RECORD 6

CONTROL LAB Cleveland T. S.

DATE 6-18-52

REX NO. 472

NAME S W P White Mildew Resisting

CARD NO. 7

POUNDS	GALLONS	MATERIAL NO.	REMARKS
300	12.6	20 or 312	Custom Sherwin-Williams Co.
75	2.3	2030	10 MATCH Standard
75	2.3	1403	
450	9.3	412	REASON FOR REVISION To show (2538) in place of (310). (2538) is (310) at 70% NVH.
60	1.1	18	
6	.7	(5094)	
47	6	(798)	
100	13	(2)	
210	28	(2538)	
121	12 3/4	(1071)	
6	3/4	(4230)	
2	1/4	(4231)	
60	9 1/4	(348)	
27	4	(141)	

VISCOSITY 30-38" 375° F	AT	HRS. AFTER GRIND
VISCOSITY #3 cmc	AT	HRS. AFTER GRIND
% SOLIDS (RUN)	ROYALTY YES ☐ NO ☐ X ☐ W ☐	
WT./GAL T 15.04	LABEL ANALYSIS CHECKED	C
BAUME 30-38	LABEL NO. RED ☐ RED ☐	
STD. OF FINENESS	NEW STD. SAMPLE REQUIRED	
NORMAL OUTPUT 100	DATE REC'D	
EST. MFG. LOSS 2%	MIL. HOLE	BLEED?
DEPARTMENT	LBS. OR GALS. PER HOUR	
PACKAGE	APPROVED	
PARALLEL NO.'S	FORMULATOR	
No Parallel	SUPT.	

0007-SWP-062096

MANUFACTURING INSTRUCTIONS:

1950-51 1863 32271

1950-51 ~~1863~~ 32271

APPLICATION: SURFACE Wood Ext.
NO. COATS one

NO. COATS one

NO. COATS one
UNDERCOATER USED Rx 151
METHOD Brush

REDUCTION: AMOUNT _____ REDUCER USED _____

REDUCER USED:

REDUCTION: AMOUNT _____ REDUCER USED _____

METHOD 2 _____

REDUCTION: AMOUNT _____ REDUCER USED _____

REDUCER USED

DRYING TIME: TOUCH 6-8hrs RECOAT 2-4 days STENCIL

HARD

SAND

HANDLE

TACK FREE

RUB

WRAP

TACK FREE RUB WRAP
BAKING TIME AND TEMP.
GLOSS Oil FILM Elastic

GLOSS Oil

FILM

Elastic

SPECIAL TESTS

Box 472

DATE	SLIP NO.	AMOUNT
May 1 - 1945	1	7-8-52
June 1 - 1945	2	"
July 1 - 1945	3	"
Aug 1 - 1945	4	"
Sept 1 - 1945	5	"
Oct 1 - 1945	6	"
Nov 1 - 1945	7	"
Dec 1 - 1945	8	"
FACTORY	FORMULA	SPEC. CARD
EXEC. COST DEPT.	11	
CLEVELAND A	11	
KENSINGTON C	11	7-8-52
ALLIED RESEARCH	11	
KENS. TECH. SERV.	11	
KENS. LACQUER	11	
NEWARK N	11	7-8-52
OAKLAND O	11	
M. SENOUR M	11	7-8-52
DETROIT D	11	
LOS ANGELES P	11	
DALLAS T	11	
DAYTON L	11	
GIBBSBORO F	11	
EXEC. MFG.	11	
CUBA H	11	
MONTREAL G	11	
BUENOS AIRES Z	11	
BRAZIL S	11	
RES ADM	11	
MEXICO	11	

0007-SWP-062097

CONTROL LAB			FORMULA RECORD 6		A135	
Cleveland T. S.			DATE 5-1-52		REX. NO. 472	
NAME S W P White Mildew Resisting					CARD NO. 6	
PCUNDS	GALLONS	MATERIAL NO.	CUSTOMER Sherwin-Williams Co. CR			
300	12.6	20 or 312	TO MATCH Standard			
75	2.3	2030	REASON FOR REVISION To reinstate as per record of Products #554 dated 4-11-52.			
75	2.3	1403				
450	9.3	412				
60	1.1	18				
6	.7	(5094)	VISCOSITY 30-38" 375° F. HRS. 1			
47	6	(798)	VISCOSITY on #3 CUP HRS. 1			
100	13	(2)	% SOLIDS (RUN)			
147	18 1/4	(310)	WT./GAL T 15.04			
			BAUME			
121	12 3/4	(1071)	STD. OF FINENESS 2-3			
6	3/4	(4230)	NO. OF SUPPLIES 100			
2	1/4	(4231)	EST. MFG. LOSS 2%			
124	19	(348)	DEPARTMENT			
27	4	(141)	PACKAGE			
			PARALLEL NO.'S			
			No Parallel			
			ROYALTY: YES ☐ ; NO ☐ ; X ☐ ; W ☐			
			LABEL ANALYSIS CHECKED C			
			LABEL NO. REDEL. RED ☐			
			NEW STD. SAMPLE REQUIRED			
			DATE REC'D			
			MILL NO. 101			
			LBS. OR GALS. PER HOUR			
			APPROVED			
			FORMULATOR			
			SUPT. S76			

0007-SWP-062098

MANUFACTURING INSTRUCTIONS:

Rex 472

APPLICATION: SURFACE Wood

NO. COATS one

UNDERCOATER USED Rx 451

METHOD 1 Brush

REDUCTION: AMOUNT

REDUCER USED

METHOD 2

REDUCTION: AMOUNT

REDUCER USED

DRYING TIME: TOUCH 6-8hrs RECOAT 2-4days STENCIL

HARD

SAND

HANDLE

TACK FREE

RUB

WRAP

BAKING TIME AND TEMP.

GLOSS

Oil

FILM

Elastic

SPECIAL TESTS

DATE	SLIP NO.	AMOUNT
<u>May - 5-2-52</u>		
<u>7-10-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
<u>1-1-52</u>		<u>11</u>
FACTORY	FORMULA	SPEC. CARD
EXEC. COST DEPT.	<u>11</u>	
CLEVELAND	<u>11</u>	
KENSINGTON	<u>11</u>	<u>5/2/52</u>
ALLIED RESEARCH	<u>11</u>	
KENS. TECH. SERV.	<u>11</u>	
KENS. LACQUER	<u>11</u>	
NEWARK	<u>11</u>	<u>5/2/52</u>
OAKLAND	<u>11</u>	
M. SENOUR	<u>11</u>	<u>5/2/52</u>
DETROIT	<u>11</u>	
LOS ANGELES	<u>11</u>	
DALLAS	<u>11</u>	
DAYTON	<u>11</u>	
GIBBSBORO	<u>11</u>	
EXEC. MFG.	<u>11</u>	
CUBA	<u>11</u>	
MONTREAL	<u>11</u>	
BUENOS AIRES	<u>11</u>	
BRAZIL	<u>11</u>	
RES ADM	<u>11</u>	
MEXICO	<u>11</u>	

CONTROL LAB

NAME S W P Gloss White Mildew Resistant

Cleveland T. S.

DATE 1-11-51

FORMULA RECORD

REV. NO. 172

CARD NO. 4

POUNDS	GALLONS	MATERIAL NO.	CUSTOMER
300	12.6	20	Sherwin-Williams Co. <i>cr</i>
75	2.3	2030	TO MATCH Standard
75	2.3	1103	REASON FOR REVISION To show Sherwin-
150	9.3	1112	Williams Mfg. Driers and also
60	1.1	18	Purchased Tallate Driers.
1.8	3.5	2052	
6	.7	(5091)	
1.7	6	(798)	
172	22 1/4	(2)	
11.7	18 1/4	(1.8) or (310)	
2	1 1/4	(911) or (910)	
6	3 1/4	(901) or (902)	
12 1/2	19	(318)	
27	11	(111)	

REASON FOR REVISION To show Sherwin-Williams Mfg. Driers and also Purchased Tallate Driers.

TEMPERATURE 28-32" @ 75°F. AT

MOISTURE 100% #3. Cup AT

% SOLIDS 15.03

WATER 15.03

BAUMER 2-3

STRENGTH 100

EST. MFG. COST 2%

DERIVATION

PACKAGE

PARALLEL NO.'S

No parallel

HRS. AFTER GRIND

HRS. AFTER GRIND

ROYALTY TEST NO. 1

LABEL ANALYSIS CHECKED

LABEL NO. RED & RED

NEW STD. SAMPLE REQUIRED

DATE REC'D

MILL Roller BLUE 7

LBS. OR GALS. PER HOUR

APPROVED

FORMULA NO.

0007-SWP-062100

MANUFACTURING INSTRUCTIONS:

CAUTION-Mixers must use respirators
and gloves when handling 2052 dry
Special label required

APPLICATION: SURFACE Wood bldg.

NO. COATS 03a

UNDERCOATER USED R-150

METHOD 1 Brush

REDUCTION: AMOUNT REDUCER USED

METHOD 2

REDUCTION: AMOUNT REDUCER USED

DRYING TIME: TOUCH 6-8hrs RECOAT 2-4 days STENCIL

HARD SAND HANDLE

TACK FREE RUB WRAP

BAKING TIME AND TEMP.

GLOSS Oil FILM Med Hard & Elastic

SPECIAL TESTS

Rex 472

DATE	SLIP NO.	AMOUNT
May 14 1957	1-12	10-3-5
J. Salas	"	"
P. Salas	"	"
Salas	"	"
Salas	"	"
Salas	"	"
Salas	"	"
Salas	"	"
FORMULA	SPEC. CARD	
EXEC. COST DEPT.	"	"
CLEVELAND	"	"
KENSINGTON	"	1-12-57 11
ALLIED RESEARCH	"	"
KENS. TECH. SERV.	"	"
KENS. LACQUER	"	"
NEWARK	"	1-17-57
OAKLAND	"	"
H. SENOUR	"	1-12-57 11
DETROIT	"	"
LOS ANGELES	"	"
DALLAS	"	"
DAYTON	"	"
CINCINNATI	"	"
EXEC. MFG.	"	"
CUBA	"	"
MONTREAL	"	"
BUENOS AIRES	"	"
BRAZIL	"	"
RES. ADM.	"	"
MEXICO	"	"

FORMULA RECORD			
CONTROL LAB	Cleveland T.S.	DATE	3/30/50
NAME	S W P Gloss White Mildew Resisting		REX. NO. 4725
			CARD NO. 3
POUNDS	GALLONS	MATERIAL NO.	CUSTOMER Sharwin Williams Co.
300	12.6	20	TO MATCH Standard
75	2.3	2030	
75	2.3	1403	
450	9.3	412	REASON FOR REVISION To show (310) as alternate for (48).
60	1.1	18	
48	3.5	2052	
6	.7	(5094)	
			VISCOSITY 28-32" @ 75 deg F. 12 HRS. AFTER GRIND
			VISCOSITY On #3 Cup 12 HRS. AFTER GRIND
47	6	(798)	% SOLIDS (RUN)
172	22 1/4	(12)	WT/GAL 15.03
147	18 1/4	(48) or (310)	BAUME
			STD. LOSS 2-3
2	1/4	(423) (94)	NEW STD. SAMPLE REQUIRED
6	3/4	(423) (90)	DATE RECD
124	19	(348)	MILL ROLLER BLEED?
27	4	(141)	LES. OR GALS. PER HOUR
			APPROVED
			FORMULATOR
			SUPT.
			PARALLEL NO.'S
			No parallel

0007-SWP-062102

MANUFACTURING INSTRUCTIONS

CAUTION-Mixers must use respirators
and gloves when handling 2052 dry
Special label required.

APPLICATION: SURFACE Wood Bldg

NO. COATS One

UNDERCOATER USED Rk 450

METHOD 1 Brush

REDUCTION: AMOUNT REDUCER USED

METHOD 2

REDUCTION: AMOUNT REDUCER USED

DRYING TIME: TOUCH 6-8hrs RECOAT 2-4days

HARD SAND HANDLE

TACK FREE RUB WRAP

BAKING TIME AND TEMP.

GLOSS Oil FILM Med. Hard & Elastic

SPECIAL TESTS

472 4/10/50

DATE	SLIP NO.	AMOUNT
4/10/50	4/10/50	
4/10/50		
4/10/50		
4/10/50		
4/10/50		
4/10/50		
4/10/50		
FACTORY	FORMULA	SPEC. CARD
EXEC. COST. DEPT.	"	
CLEVELAND	"	
KENNINGTON	"	4/10/50
ALLIED RESEARCH	"	
KENS. TECH. SERV.	"	
KENS. LACQUER	"	4/10/50
NEWARK	"	4/10/50
OAKLAND	"	4/10/50
M. SENOUR	"	
DETROIT	"	
LOS ANGELES	"	
DALLAS	"	
DAYTON	"	
GIBBSBORO	"	
EXEC. MFG.	"	
CUBA	"	
MONTREAL	"	
BUENOS AIRES	"	
BRAZIL	"	
SES ADM.	"	

0007-SWP-062103

FORMULA RECORD			
CONTROL LAB		Cleveland T.S.	DATE 6/16/49
NAME		S W P Gloss White Milcow Resisting	
		REX NO.	472
		CARD NO.	2
POUNDS	GALLONS	MATERIAL NO.	CUSTOMER Sherwin Williams Co.
300	12.6	20	TO MATCH Standard <i>ln</i>
75	2.3	2030	
75	2.3	1403	REASON FOR REVISION Taking formula up to
450	9.3	412	date per MVL's letter of 6/3/49
60	1.1	18	
48	3.5	2052	
6	.7	2270 (507)	VISCOSITY 28-32" @ 75 deg F. HRS. AFTER GRIND
			VISCOX On #3 Cup HRS. AFTER GRIND
47	6	(798)	% SOLIDS RUN ROYALTY YES ☐ NO ☐ X ☐ V ☐
172	22 1/4	(2)	WT. GAL T 15.03 LABEL ANALYSIS CHECKED DATE 12-21-49
147	18 1/4	(48) (312)	LABEL NO. RED ☐ RED ☐
			NEW STD. SAMPLE REQUIRED
2	1/4	(4231)	DATE REC'D
6	3/4	(4230)	EST. MFG. LOSS 22% MILL Roller BLEED?
124	19	(348)	DEPARTMENT LBS. OR GALS. PER HOUR
27	4	(141)	PACKAGE APPROVED
			PARALLEL NO.'S FORMULATOR <i>[Signature]</i>
			SUPT. <i>876</i>

0007-SWP-062104

FORMULA RECORD			A135 GREEN 3-15-47	
Exp. No.	Date	8-22-45	Class	6 TG
Name	S W P Gloss White-Mildew Resistant		Card No.	1
Replaces No.				
POUNDS	GALLONS	MATERIAL No.	Customer S.W. Trade Sales	
260		20 L or F. only	Match Treated-SW T.S.	
146		1403	3.5% in oil / 1/2 in water	
470		412	Reason for Revision per V. Mills letter	
162		BW 10 3	7/30/45 Subj. Realigning Trade	
48		2052	Sales Rex. numbers.	
POISON			SUPERSEDES REI-63057	
			Viscosity 20-32° 275° #3 at 57 hrs. after grind	
			Viscosity at hrs. after grind	
			% Solids (Run)	
			WL/Gal 15.35	
			Baume	
			Std. of Fineness 35	
			Normal Output 100	
			Est. Mfg. Loss 2%	
			Department	
			Package	
			Parallel No.'s	
			Royalty: Yes ☐ ; No ☐ ; X ☐ ; W ☐	
			Label Analysis Checked-Date	
			Label: No Red ☐ Red ☒	
			New Std. Sample Required	
			Date Rec'd	
			Mill	
			Bleed?	
			Lbs. or Gals. per hour	
			Approved	
			Formulator ORJogd per	
			Supt.	

NO SUBSTITUTIONS TO BE
MADE IN THIS FORMULA.

0007-SWP-062106

MANUFACTURING INSTRUCTIONS:

NOTE:

(POISON)

Mixers to use respirators & gloves when handling 2052 dry.

Application: Surface Special label req. red...

Undercoater Used No. Coats

Method 1

Reduction: Amount Reducer Used

Method 2

Reduction: Amount Reducer Used

Drying Time: Touch Recoat Stencil

Hard Sand Handle

Tack Free Rub Wrap

Baking Time and Temp.

Gloss Film

Special Tests

DATE

SLIP No.

AMOUNT

FACTORY

FORMULA

SPEC. CARD

Exec. Cost Dept.

Cleveland

Kensington

Allied Research

Kens. Tech. Serv.

Kens. Lacquer

Newark

Oakland

M. Senour

Detroit

Los Angeles

Dallas

Dayton

Gibbsboro

Pittsburgh

Cuba

Montreal

Buenos Aires

Brazil

0007-SWP-062107

TO MATCH StandardREL. NO. 1-72-11-533CARD NO. 10DATE 10-28-53APPLICATION: SURFACE Wood Ext.NO. COATS one

UNDERCOATER USED

METHOD 1 Brush

REDUCTION: AMOUNT

REDUCER USED

METHOD 2

REDUCTION: AMOUNT

REDUCER USED

DRYING TIME: TOUCH 6-8hrs RECOAT 2-4days SPENCIL

HARD

SAND

HANDLE

TACK FREE

RUB

WRAP

BAKING TIME AND TEMP.

GLOSS Oil

FILM

Elastic

SPECIAL TESTS

DATE 10-28-53 CLIP NO. 1 AMOUNTQuint Control

0007-SWP-062089

FORMULA RECORD			6	135
CONTROL LAB Cleveland T. S.			DATE 6-12-53	REX NO. 172
NAME S W P Mildew Resisting White			CARD NO. 9	
POUNDS	GALLONS	MATERIAL NO.	CUSTOMER Sherwin-Williams Co.	
300	12.6	312	MFG. INSTR. Up to 2 gals of (348)	
75	2.3	2030	permitted to adjust Viscosity.	
75	2.3	1403		
450	9.3	112		
60	1.1	18		
6	.7	(5094)		
47	6	(798)	WT./GAL T 15.0	
100	13	(2)	GRIND 2-3H	
210	28	(2536) or *	OUTPUT 100	
			MFG. LOSS 2%	
121	12 3/4	(1071)	STOR. LOC.	
6	3/4	(4230)	SOLIDS	
2	1/4	(4231)	PARALLELS	
27	4	(111)	No Parallels	
60	9 1/4	(348)	REASON FOR REVISION Show use of (2536) & (2539) and adjust Viscosity.	
See Mfg. Instructions:				
* 18 1/4 gals (2539)				
9 3/4 gals (348)			FORMULA NO. 3 Thompson SUPT. 876	