Howard Spellman

M. H. DETRICK COMPANY
Laboratory

PLAINTIFF'S EXHIBIT
MHD- 95

July 29, 1959

T. S. Clousing
Chicago Office

Dear Ted:

On June 3, 1959 we tested two samples of our "Griptex Block" in our muffle furnace at 1900°F for sixteen hours. We obtained the following results:

Weight Loss - 4.6%

Volume Loss - 7.0%

Linear Shrinkage

Length	-	2.3%
Thickness	-	2.9%
Width	-	4.2%

Color change - Dark to light tan.

Very truly yours,

LABORATORY

Bruce

R. Bruce Abell

RBA:rt