THERMINOL® 55 HEAT TRANSFER FLUID

A low cost synthetic fluid for use in liquid phase up to 600 °F. without system pressurization.

TECHNICAL BULLETIN T-55

"Nothing contained herein is to be construed as a recommendation to use any product in conflict with any patent. MONSANTO MAKES NO WARRANTIES AS TO THE FITNESS OR MERCHANTABILITY OF ANY PRODUCTS REFERRED TO, no guarantee of satisfactory results from reliance upon contained information or recommendations, and disclaims all liability for any resulting loss or damage."

Monsanto

FUNCTIONAL FLUIDS | Monsanto Company, 800 North Lindbergh Blvd., St. Louis, Missouri 63166

DSW 552831

STLCOPCB4091248

Therminol® 55 is a low-cost synthetic heat transfer fluid developed for use in non-pressurized, indirect heating systems. Added to the extensive Monsanto line of heat transfer fluids to meet exacting needs, Therminol 55 demonstrates thermal stability superior to that of hydrocarbon oils of comparative cost.

System start-up at temperatures as low as 0°F. is possible, due to the low temperature viscosity characteristics of Therminol 55. It can be used at temperatures up to 600°F. At 550°F. and below, the fluid has extremely long life.

Therminol 55 systems should be blanketed with an inert atmosphere to minimize fluid oxidation. A system relief valve should also be provided.

Unlike the Therminol FR (fire-resistant) fluids, Therminol 55 can support combustion.

For detailed system information, contact your local Monsanto sales office, or write to: Monsanto Company, Functional Fluids, 800 N. Lindbergh Blvd., St. Louis, Mo. 63166.

TYPICAL PROPERTIES OF THERMINOL® 55

Composition	Alkylated Aromatics
Appearance	Clear Brown Liquid
Odor	Odorless
Pour Point	—20°F.
Flash Point	355°F.
Flame Point	410°F.
Autoignition Temperature	670°F.
Refractive Index	n_{25}^{D} 1.5035
API Gravity 60/60	26.6
Specific Gravity g/cc	0.895
Lb./gallon	7.5
Average Molecular Weight	340

FLUID PROPERTIES OF THERMINOL 55

Temp. °F.	Density gm/cc	Kinematic Viscosity cs	Specific Heat BTU/Lb.-°F.	Thermal Conductivity BTU/hr.-ft.-°F.	Vapor Pressure mm Hg
0	0.9148	1610.0	0.420*	0.0813*	—
100	0.8775	30.1	0.472	0.0784	0.5*
200	0.8403	5.0	0.522	0.0753	3.0
300	0.8031	2.10*	0.572	0.0724	10
400	0.7658	1.18	0.620	0.0692	40
500	0.7286*	0.80*	0.670	0.0661*	100*
600	0.6913*	0.60*	0.718*	0.0630*	250*

*Extrapolated Data

DSW 552832

STLCOPCB4091249

SPECIFIC HEAT AND THERMAL CONDUCTIVITY



SPECIFIC GRAVITY



DSW 552833

STLCOPCB4091250

KINEMATIC VISCOSITY



VAPOR PRESSURE



DSW 552834

2-2828-0469-6 LITHO IN U.S.A.

STLCOPCB4091251