

Table II

Length Distribution of Chrysotile Fibers in Brake Drum Dust

Fibers counted and sized at 42,000X
(all fibers have diameters from 250Å to 500Å)

<u>Sample</u>	<u>750-1500Å</u>	<u>1500-2250Å</u>	<u>2250-3000Å</u>	<u>3000-3750Å</u>	<u>Total</u>
1	40%	34%	11%	11%	96%
2	32	23	32	-	87
3	20	25	25	-	70
4	26	37	26	7	96
5	57	17	4	-	78
6	23	9	12	12	56
7	50	26	21	2	99
8	29	30	21	17	97
9	6	41	18	10	75
10	11	6	31	31	79

8005 1889

PRODUCED BY FORD