

FORMULA RECORD				TEMPORARY FORMULA	
Exp. No. _____		Date <u>2-26-36</u>		Rev. No. <u>305</u>	
Name <u>AMILY PAINT YELLOW</u>		Card No. <u>6</u>		See No. <u>5</u>	
150 LBS.	461 C	Customer	Trade Sales		
150 "	1526	To Match	Established Product		
260 "	20 L				
22 "	12310	Weight Per Gal.	T 12.80 Visc.		
165 "	19	Baume	Std. of Fineness <u>2 M</u> ☐ Red		
"		<u>35</u> Gals. per hour	<u>30"</u> Mill. ☒ No Label Required		
"	<u>1067# Base</u>	New Std. Sample Required	<u>Yes</u> Date Rec'd. _____		
"		Reason for Revision	<u>Temporary formula to utilize purchased oil.</u>		
27 GALS. (<u>2</u>)			<u>Retain present formula for use when temporary formula not effective.</u>		
9 " (<u>1762</u>)					
6 " (<u>38</u>)					
" (<u> </u>)					
20 " (<u>38</u>)					
8 " (<u>429</u>)		Normal Output	<u>100</u> Approved <u> </u>		
6-1/2 " (<u>348</u>)		Est. Mfg. Loss	<u>2%</u> Formulator <u> </u>		
" (<u> </u>)		Department	<u>B</u> Supl. <u> </u>		
" (<u> </u>)		Label Analysis Checked-Date	_____ A135		

MANUFACTURING INSTRUCTIONS:							
Hiding Power - Good							
Reduction: Amount		Reducer Used		PRODUCTION			
Application: Surface		Method					
No. Coats		Undercoater Used		Date	Slip No.	Amount	
Drying Time: Touch		Handle					
Rub		Wrap					
Baking Time and Temp.		Stencil					
Gloss		Film					
Special Tests							
FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND	<u>2-28-36</u>			ALLIED RESEARCH	<u>2-28-36</u>		
NEWARK	.			GIBBSBORO			
KENSINGTON	.			DAYTON			
OAKLAND	.			DETROIT			
DALLAS	.			LONDON			
LOS ANGELES	.			AUSTRALIA			
MONTREAL	.						
COSTA MESA	.						

FORMULA RECORD

Exp. No. *11-75* Date *11-1-35* Rex. No. *305*
 Name *Family Pt. Yellow* Card No. *5* See No. *4*

150	LBS	46LC	Customer	Trade Sales
150	"	1528	To Match	Established Product
260	"	20 L		
22	"	12510	Weight Per Gal.	<i>12.80</i> Visc. <i>19-22" #3 (10.5-21-40 p.u. H.T.S.)</i>
165	"	19	Baume	Std. of Fineness <i>2 M</i> ☐ Red ☒ No Label Required
"	"	"	<i>35</i> Gals. per hour	<i>30"</i> Mill
"	"	<i>1047# Base</i>	New Std. Sample Required	<i>Yes</i> Date Rec'd <i>5-4-36</i>
"	"	"	Reason for Revision	<i>To reduce grinding expense.</i>
27	GALS.	(2)		
6	"	(213)		
6	"	(38)		
"	"	()		
20	"	(38)		
8	"	(429)		
9-1/2	"	(348)		
X	"	()		
"	"	()		

VOID

Normal Output *100* Approved *JAN* Formulator
 Est. Mfg. Loss *2%* BY *BV* Supt. *H. B. G. R. B.*
 Department *B* Label Analysis Checked - Date *11-1-35*

A135 9-35 2538

MANUFACTURING INSTRUCTIONS: *when revision rec'd Card # 4 of transfer file*

Hiding Power: Good

Reduction: Amount	Reducer Used	PRODUCTION		
Application: <i>Wood or Metal, Top or Surface</i>	Method: <i>Brush</i>	Date	Slip No.	Amount
No. Coats: <i>Solid Two</i>	Undercoater Used: <i>Primer for New Work</i>			
Drying Time: <i>Touch 8-12 hrs. Handle</i>	Recoat: <i>18-24 hrs.</i>			
Rub: <i>Sand</i>	Wrap: <i>Stencil</i>			
Baking Time and Temp.				
Gloss: <i>Gil</i>	Film: <i>Tough</i>			
Special Tests				

FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE	FACTORY	FORMULA	SPEC. CARD	STD. SAMPLE
CLEVELAND	<i>11-6-35</i>	<i>2-27-42</i>		ALLIED RESEARCH	<i>11-6-35</i>	<i>2-27-42</i>	
NEWARK				GIBBSBORO			
KENSINGTON				DAYTON	<i>3-7-38</i>	<i>11</i>	
OAKLAND				DETROIT			
DALLAS				LONDON			
LOS ANGELES				AUSTRALIA			
MONTREAL							

0007-SWP-061080

FORMULA RECORD			
CONTROL LAB		Gibbsboro	DATE 12-1-49
NAME		Sultana Light Brown	LUCASEY NO. 305
			CARD NO. 1
POUNDS	GALLONS	MATERIAL NO.	CUSTOMER EXPORT
2	.22	547	TOM TCH Key 63560
85	1.75	412	
55	1.62	1133	REASON FOR REVISION
4	.07	12311	NEW
4	.12	134	
250	11.88	2203	
320	42	FV 74	VISCOSITY 25-35" #3 cup
15	2	(1230)	AT HPS, AFTER GRIND
34	1/2	(1231)	VISCOSITY AT HPS, AFTER GRIND
34	1/2	(4-32)	% SOLIDS (RUN)
13	2	(3/8)	ROYALTY YES; NO; X; O; V; O
			ST. GALT 10.1
			LABEL ANALYSIS CHECKED DATE
			BRUNE
			LABEL NO. RED; RED; RED
			STD. OF FINENESS 3
			NEW STD. SAMPLE REQUIRED yes
141	19	(28/8) E	DATE REC'D
133	20 1/2	(3/8)	MILL Ball-18 hrs
			EST. HPG. LOSS 2%
			DEPARTMENT
			PACKAGE
			PARALLEL NO.'S
			Box 63560
			FORMULATOR D. H. Howe
			SUP. D. F. H. Howe