

MO-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-908-D LOT 34928

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
	1	1822	T-54	
	1	1868	T-127	

STUMP

TOTAL NET WT. 3690 PKG. N-CODE _____

PROD. SPVR _____ DATE _____ WHSE. OPER. _____

PH 312186 _____

N 27518

23
344

CG 03 CODE KY-908-D PKG.
 → MAR 17 34928
 EST. WGT. 949 LBS.

TOTALS

OK
KP

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES KY-908-D (D) APPROVED BY
EWK 12/12/77
DCG 12/14/77

TYPED BY
rj 1/31/78
MAKING NOTES

REMARKS

TOTAL WGT. 3549#

NAME: DROLOR® YELLOW- LIGHT

NON-BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

VAT	244					PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	3-18-80					STARTED	8 AM				
TIME	7:30 AM					CAKES USED	46				
RELEASED BY	C. M.					WATER ON	10:30 AM				
PRESS	2	22	23	24		HRS. WASHED	2				
NO. OF CAKES	46	46	46	52		OHMS	2000				
PRESS WITH						HRS. WASHED					
WASH TO	2000					OHMS					
TEST AFTER	2					HRS. WASHED					
LOAD	On 6 cars					OHMS					
						CAKE CONDITION	5				
						NO. CARS LOADED	5				
						EXPLAIN LOSSES					

SAMPLES 8 oz Jar
DELIVER TO CIL FOR COLOR

SAMPLED BY [Signature] RELEASED BY C.C.

- DRYING -

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATE

Dry on first stage only.
Reset every 5 hrs. til dry.

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

NO. DRUMS 12
LUMP WGT. 3638
RELEASED BY [Signature]

- GRINDING -

MILL 939 HSP 1/8" RP SCREEN 3500 RPM
MAX. TEMP. 170°F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT Can
DELIVER TO CIL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050094631

N 27518.01

.00
349.28
.41
.18
.00

3.23
.14
3.08
.14
3.15
.14
3.21
.14
- 3.24
.14
3.15
.14
3.28
.14
3.12
.14
- 3.14
.14
3.26
.14
3.24
.14
2.96
.14
363.8