

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE Y7808 LOT 37412

NET WT/PKG NO. PKG PACK. WGT LOCATION PG

15 2048 43TOTAL NET WT. 2048 STUMP 2040 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

10/1/61 292

N35191

D.T

146.+
142.+
138.+
140.+
148.+
149.+
134.+
138.+
142.+
134.+
136.+
137.+
124.+
145.+
95.+
2048.T

CO 46 CODE YT-808-D PKG.

OCT 13 80 37412
EST. WGT. 2238 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
YT-808-D (D)
APPROVED BY
EWK 9/28/77
BBK 10/17/77
DCG 10/17/77

TYPED BY
JIC 10/26/77
MAKING NOTES

REMARKS

15

NAME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS

- PRESSING -

RECORD

AT 106
DATE 10-13-80
TIME 5:35 PM
RELEASED BY
PRESS 32 33 35
D. OF CAKES 60 62 60
PRESS WITHOUT AGITATION
ASH TO 4000 OHMS with 35-75°F water
ENT AFTER 4 HOURS
DAD on 9 cars

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO. CARS LOADED 8

EXPLAIN LOSSES
RECORD TEMP 168°F AT START
OF PRESSING

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY

- DRYING -

DRY 24 HOURS AT 200°F

LUMP: - OK - WET - SALTS - CONTAMINAT

No result of any processing
Losses

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY
NO. DRUMS 13
LUMP WGT. 5090
RELEASED BY RH

- GRINDING -

ILL 4 or 10 HSP 1/8" RBCREEN 3500 RPM
MAX. TEMP. 190 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 env + 1 Pint can
DELIVER TO C T L

DATE MIXED
SAMPLED BY 149-10115280 RELEASED BY

37412
51
16

0.00 *
1.69 +
0.14 ✓
1.85 +
0.14 ✓
1.75 +
0.14 ✓
1.75 +
0.14 ✓
1.80 +
0.14 ✓
1.76 +
0.14 ✓
1.70 +
0.14 ✓
1.70 +
0.14 ✓
1.73 +
0.14 ✓
1.73 +
0.14 ✓
1.82 +
0.14 ✓
1.91 +
0.14 ✓
1.03 +
0.14 ✓
20.40 *