MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY788 LOT 36246

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1876	1	T-7		
1728	1	T-23		
~~STUMP~~ Lump - 3,664				

TOTAL NET WT. 3604 PKG. N-CODE

PROD. SPVR. RH DATE 6,26,80 WHSE. OPER.

N32216

23

240

CG 03 CODE KY-788-D PKG. ____

→ 36246

EST. WGT. 960 LBS.

TOTES OK AP

Total Wgt. 3560# Req(____)

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/77
	DCG 9/27/77
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

NAME: "KROLOR" YELLOW - LIGHT NON-BLEEDING

EC 240

INSTRUCTIONS						-PRESSING- RECORD					
AT	240					PRESSLOAD	1ST	2ND	3RD	4TH	5T
DATE	6-23-80					STARTED	8A				
TIME	2:30 PM					CAKES USED	3				
RELEASED BY	JAA					WATER ON	2:30				
PRESS	22	23	24			HRS. WASHED	8				
NO. OF CAKES	46	46	46			OHMS	2000				
PRESS With AGITATION						HRS. WASHED					
WASH TO 2000 OHMS with 35-75°F water						OHMS					
TEST AFTER 2 HOURS						HRS. WASHED					
LOAD on 6 cars						OHMS					
						CAKE CONDITION	9				
						NO. CARS LOADED					
						EXPLAIN LOSSES					
SAMPLES 1- 8oz JAR						SAMPLED BY		RELEASED BY			
DELIVER TO CTL for Color											

-DRYING-

Dry 12 hrs at 220 °F
Then Dry 8 hrs at 160 °F

LUMP: - OK - WET - SALTS - CONTAMINAT

Color appears dry.

ADDITIONAL DRYING HOURS REQUIRED

No Drums 15

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 3664
RELEASED BY JAA

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °F

SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE / WITHOUT MIXING
SAMPLES 1 Env. & 1 PE can
DELIVER TO C T L

DATE MIXED
SAMPLED BY RELEASED BY

N32216.01

DUP050457118





N32216.02

DUP050457119

36246
41
225

0.00 *

2.75 +
0.14 -
2.80 +
0.14 -
2.65 +
0.14 -
2.72 +
0.14 -
2.80 +
0.14 -
2.68 +
0.14
2.72 +
0.14 -
2.59 +
0.14 -
2.70 +
0.14 -
2.83 +
0.14 -
2.73 +
0.14 -
2.55 +
0.14 -
2.59 +
0.14 -
2.50 +
0.14 -
1.13 +
0.14 -
36.64 *

N32216.03

DUP050457120