MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)


CODE YT868 LOT 37776

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
	14	2192	33	
	STUMP	LUMP	214	

TOTAL NET WT. 2192 PKG. N—CODE

PROD. SPVR. DATE WHSE. OPER.

N35295



DUP050108413

#1 Membrane

CG 46 CODE YT-868-D PKG. ____

→ Nov-6 80 37776

EST. WGT. ~~2253~~ 2241 LBS.

84" @ Start

Temp 165°F.

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	YT-868-D (A)	EWK 9/30/76
		EAS 5/26/78
		DCG 5/30/78
	TYPED BY	

MAKING NOTES

REMARKS

NAME: DALAMAR® YELLOW

INSTRUCTIONS					-PRESSING- RECORD					
VAT	106				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	11-6				STARTED	6:50	7:45	Vat worked in		8:30 AM
TIME	6:45 AM				CAKES USED	31	31			
RELEASED BY	237				WATER ON	8:45				
PRESS	32	33	35		HRS. WASHED	2 1/4	Equipment started 12:45		Finished 2 PM	
NO. OF CAKES	60	60	60	(62)	OHMS	3008		including draining of		
PRESS without AGITATION					HRS. WASHED	2 3/4		membrane		
WASH TO 4000 OHMS with 35-75°F water					OHMS	3650		215 PSI + attained before		
TEST AFTER 6 HOURS					HRS. WASHED	3 3/4		relief valves presented		
LOAD on 10 cars					OHMS	5000		high pressure		
					CAKE CONDITION					
					NO. CARS LOADED	7				
DO NOT LOAD BOTTOM 2 ROWS OF CARS					EXPLAIN LOSSES					

SAMPLES
DELIVER TO

SAMPLED BY RELEASED BY

-DRYING-

DRY - 30 HOURS AT - 180 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 13

SAMPLES
DELIVER TO

NO. CARS PULLED
SAMPLED BY

LUMP WGT. 2148
RELEASED BY

-GRINDING-

MILL 4 or 10 HSP1/8"RP SCREEN 3500 RPM
MAX. TEMP. °F


SCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES /ENV + 1 PT can [redacted]
DELIVER TO C T L

DATE MIXED 11-17-80
SAMPLED BY
RELEASED BY

DUP050108414



DUP050108415