

Trade Name: Quality Mixed
 Category: Semi-Gloss Finish
 Color: White
 Number: 2047
 Quality: second

	lbs.	Gals	Unit Cost	Total Cost
Pigment: 60 %				
Lithopone	410	11.4	4.34c	17.79
Titanox	328	12.6	5.61c	18.40
Cal. Whiting	82	3.6	.492 c	.40
Vehicle: 40%				
Varnish	410	54.7	.91g	49.78
Drier	27	3.9	.37g	1.41
Turpentine	27	3.8	.68g	2.58
Distillate	82	12.0	.058g	.70
Calculated Yield	1366	102.0		91.09
Manufacturing Loss		2.0		
Actual Yield		100.0		

Cost Analysis:

Material cost per 100 gallon	91.09
Direct Labor	4.05
Factory Overhead	16.80
Bulk cost	111.94
Complete package cost	18.12
Factory cost in package per 100 gallon	130.06
Factory cost in package per gallon	1.30

PRICES

Show the highest net unit price which was charged or which would have been charged in March 1942, to each of the Following types of Buyers or Transferees:

- (A) To a company owned or controlled outlet
- (B) to an Independent Wholesaler
- (C) By Company owned or Controlled outlet to Retail Customer
- (D) To an Independent Retailer (Dealer)
- (E) To other (Specify) *PARENT CORPORATION OUTLET*

N 4496