MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-788 LOT 34991

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
50	69	3,450		
	STUMP			

TOTAL NET WT. 3,450 PKG. N–CODE 1,30

PROD. SPVR.	DATE	WHSE. OPER.
[illegible]	3/24/20	

DUP050094440

CG 03 CODE KY-788-D PKG. ____

→ MAR 21 34991

EST. WGT. ~~960~~ 860 LBS.

OK
HP

23/244

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-788-D (J)	EWK 9/22/76
	DCG 9/27/76
TYPED BY	
NE 2/17/77	

MAKING NOTES

REMARKS

Total Wgt. ~~3560~~ 3460# Req(_____)

NAME: "KROLOR" YELLOW - LIGHT

NON-BLEEDING

-PRESSING-

INSTRUCTIONS

VAT	244				
DATE	3-22-80				
TIME	6:15PM				
RELEASED BY	BD				
PRESS	22	23	24		
NO. OF CAKES	46	46	46		

PRESS With AGITATION

WASH TO 2000 OHMS with 35-75°F water

TEST AFTER 2 HOURS

LOAD on 6 cars

SAMPLES 1- 8oz JAR

DELIVER TO CTL for Color

RECORD

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	7:30PM				
CAKES USED	54				
WATER ON	3:30PM				
HRS. WASHED	5½				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION	7				
NO. CARS LOADED					

EXPLAIN LOSSES

SAMPLED BY #469 RELEASED BY

-DRYING-

Dry 12 hrs at 220 °F H.V. H.V.

Then Dry 8 hrs at 160 °F °F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

No Drums 14

SAMPLES

DELIVER TO

NO. CARS PULLED LUMP WGT. 3466

SAMPLED BY RELEASED BY

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM

MAX. TEMP. 150 °F

SCREEN RPM

MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING

SAMPLES 1 Env. & 1 Pt can

DELIVER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050094441



DUP050094442