

CC 01 CODE YE-698-D PKG

LOT MAY -0.81-E1503

EST'D WGT 3371

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSED APPROVED BY
YE-698-D (R) F. POST-4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPR

INSTRUCTIONS

= PRESSING =

RECORD

VAT
DATE
TIME
RELEASED BY
PRESS 2 91 92 93
NO. OF CAKES 32 42 32 32
PRESS WITH AGITATION
WASH TO 2000 OHMS 35-74 F WATER
TEST AFTER 2 HOURS
LOAD ON 4 CARS

PRESSLOAD
STARTED
CAKES USED
WATER ON
HRS. WASHED
OHMS
HRS. WASHED
OHMS
HRS. WASHED
OHMS
CAKE CONDITION
NO CARS LOADED
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 12 HOURS AT 240 DEG F
(NOT EXTRUDED) DRY 14 HOURS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO CTL

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST GATE AT "9" FOR HIGH
AIR FLOW

RPM SCREEN
MAX. TEMP. RPM
F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1503
41
16

0.00 *

3.24 +
0.12 ✓
3.39 +
0.12 ✓
3.12 +
0.12 ✓
3.29 +
0.12 ✓
3.34 +
0.12 ✓
2.96 +
0.12 ✓
3.33 +
0.12 ✓
3.53 +
0.12 ✓
3.26 +
0.12 ✓
3.27 +
0.12 ✓
2.03 +
0.12 ✓
33.44 *