

Vinyl Sample Results

Date

11-25-01

Product	Blend #	PARTICLE SIZE										Past 140	HP	Bulk Density	Fluff	Flow	"L" Color	"B" Color	FTIR	PVA	RVCM	Reactor	Run Time
		Micron	40	60	80	100	120	140	200	Pan													
5395	1012540																		70/37	1411	400	418	
5385	1012670	→ 204	0	18.2	44	18.3	88	3.2	2	0.5	24			.556	.543	6.9	98.44	1.98	248	173	1807	700	330
5395	1012730																		67/33	1409	300	416	
5395	1012860	→ 145	0	2.4	31.6	30	20.4	9	5.5	0.8	6.2	3/1		.516		7.4	98.46	1.63	404	63/35	1408	600	411
5395	1012950																		63/34	1410	500	417	
5395	1013040																		69/34	1410	400	411	
5385	1013170	→ 207	0	19.1	50.9	17.6	7.9	2.7	1.5	0.4	1.9			.580	.409	6.5	98.43	1.89	377	171	1810	700	337
5395	1013230																		67/33	1411	300	411	
5395	1013360																						
5395	1013450	→ 146	0	2.5	31.5	30.6	21.6	8.6	4.4	0.8	5.2	3/1		.512		7.1	98.5	1.63	230	67/36	1409	500	414
5395	1013540																			69/33	1408	400	413
5385	1013670	→ 201	0	16.1	49.5	18.9	9.3	3.6	2.3	.5	2.8			.517	.603	6.9	96.8	2.1	321	174	1808	700	340
5395	1013730																			64/33	1410	300	419
5395	1013860	→ 151	0	1.6	19	27.7	25.6	14.3	10.1	1.7	11.8	3/1		.525		7.9	98.5	1.6	516	65/33	1410	600	408
5395	1013950																			60/33	1410	500	414
5395	1014040																			64/33	1409	400	410
5385	1014170	→ 195	0	15	45	18.8	11	5.3	4.1	.8	4.9			.572	.612	6.8	97.2	2.2	618	177	1808	700	332
5395	1014230																			69/37	1408	300	408
5395	1014360	→ 183	0	12	38.5	18.6	14.1	8.7	7.3	.8	8.1	50/3		.545		7.1	96	2.2	83	63/36	1408	600	413
	Recheck →																						
														</									