

→ Kanyab

VINYL CHLORIDE PRODUCT QUALITY REPORT

ETHYL CORPORATION — BATON ROUGE PLANT

9611

CUSTOMER'S
NAME

Monanto

CAR NO. <u>WTLX 84211</u>	SALES ORDER NO. <u>27468</u>	DATE LOADED	DATE SHIPPED <u>7-29-64</u>
---------------------------	------------------------------	-------------	-----------------------------

APPEARANCE:

SUSPENDED MATTER NONE; COLOR Colorless; CLARITY clear

POLYMER

CONVERSION % 98.8

RELATIVE VISCOSITY OF POLYMER

(1% in Cyclohexanone) 2.87

DORELL WEATHERING TEST AT °C @	3.0 ML	<u>0.00</u>
	2.0 ML	<u>0.00</u>
	1.0 ML	<u>0.00</u>
	0.5 ML	<u>0.00</u>

I M P U R I T I E S	ACETYLENE (PPM)	<u>0.1</u>
	ACIDITY (PPM AS HCL)	<u>0.0</u>
	ACETALDEHYDE (PPM)	<u>0.2</u>
	IRON (PPM)	<u>0.1</u>
	INHIBITOR (PHENOL-PPM)	<u>0</u>
	PEROXIDE (PPM AS H ₂ O ₂)	<u>0.02</u>
	NON-VOLATILE (PPM)	<u>7</u>
	SULFUR (PPM)	<u>0.0</u>
	WATER (PPM)	<u>15</u>

REMARKS

CBY 1112433

ANALYST

J. V. Tobias

BR-847A REV. 10-64

RSV0032153