

CG 16 CODE RT-5-D PKG.

OCT 18 K2K52

EST. WGT: 2419 LBS.

PROCESSES	APPROVED BY
RT-795-D (M)	B8K 10-19-77
Alternate	DCG 10-28-77
TYPED BY	
JIC 11-7-77	
MAKING NOTES	

REMARKS

NAME: MONASTRAL® *WPOLET R*

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

AT					181	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
ATE					10-19-77	STARTED	8:30 AM				
DATE					8:10A	CAKES USED	58				
RELEASED BY					60	HOURS TO FILL					
RESS	13/14	15/16	38	39	33						
C. OF CAKES	6 x 42	6 x 42	60	60	60						
PRESS	WITH	AGITATION									
WASH TO	-	OHMS									
TEST AFTER	-	HOURS									
LOAD	ON 8 CARS										

CAKE CONDITION

NO. CARS LOADED

EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

DRY 20 HOURS AT 220°F

LUMP: - OK - WET - SALTS - CONTAMINATED
DRYER SECTIONS:

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BY

NO. DRUMS

LUMP WGT.

RELEASED BY

-GRINDING-

MILL 1 HSP 0.066 RP SCREEN 3480 RPM
MAX. TEMP. 140 °FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env + 1 Pint Can

DELIVER TO C.T.L.

DATE MIXED 10-25-77

SAMPLED BY 389

RELEASED BY

52
124
51

9.2000. Drump
14. Drump

1.76 +
0.14 -
1.78 +
0.14 -
1.82 +
0.14 -
1.79 +
0.14 -
1.87 +
0.14 -
1.90 +
0.14 -
1.93 +
0.14 -
1.82 +
0.14 -
1.89 +
0.14 -
1.92 +
0.14 -
1.89 +
0.14 -
1.90 +
0.14 -
1.98 +
0.14 -
1.99 +
0.14 -
24.28 *