

225

	PROCESSES	APPROVED
	(D) YC-5-A	ENK 9/23/
	ALTERNATE	DCG10/ 6/
	TYPED BY	
	NE 3/5/77	
MAKING NOTES		
REMARKS		

NAME: "DALAMAR" YELLOW					BLEEDING					
INSTRUCTIONS					-PRESSING-		RECORD			
TAT 105					PRESSLOAD		1ST	2ND	3RD	4TH
DATE 5-8-81					STARTED		3PM			
TIME 11:30A					CAKES USED		60			
RELEASED BY S.B.					WATER ON		6PM			
PRESS 98 98 98 (A-1)					HRS. WASHED		6:00			
NO. OF CAKES 98 98 98					OHMS		4000			
PRESS with OUT AGITATION					HRS. WASHED					
WASH TO 4000 OHMS with 35-75°F water					OHMS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD in metal drums at 325# net/drum					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED					
Air blow press cake for 15 min at 40 PSI					EXPLAIN LOSSES					
SAMPLES 1-8oz JAR					SAMPLED BY		RELEASED BY			
DELIVER TO cti for color										
-DRYING-										
HOURS L.V. H.V.					LUMP: - OK - WET - SALTS - CONTAMIN					
TEMP. °F °F										
DO NOT DRY										
SAMPLES					NO. CARS PULLED		LUMP WGT.			
DELIVER TO					SAMPLED BY		RELEASED BY			
-GRINDING-										
MILL SCREEN RPM					SCREEN		RPM			
MAX. TEMP. °F					MAX. TEMP.		°F			
SAMPLE AFTER / WITHOUT MIXING					DATE MIXED					
SAMPLES										
DELIVER TO C T L					SAMPLED BY		RELEASED BY			