

SPECIFICATION FOR PURCHASED MATERIAL

Material Basic Silicate WhiteDate 5/13/68Code 68 03 20Lead - Eagle Picher 202

Supersedes Specification

General Description:

Date _____ Code _____

White free flowing powder

CHARACTERISTICS	MIN.	STD.	MAX.	TEST METHOD
1. Color	Equal	to Standard		ASTM D 387
2. Texture	Equal	to Standard		
3. Oil Absorption	17		19	ASTM D 281
4. Residue 325 Mesh			1.0	ASTM D 185
5. Moisture (%)			.75	ASTM D 280

SPECIAL TESTS AND/OR CHARACTERISTICS:

N16343

0007-SWP-063034

Code 68...

RAW MATERIAL CHARACTERISTICS AND ASSIGNMENT REQUEST FORM

INTRA COMPANY CONFIDENTIAL

This Side for S-W and Affiliated Company Personnel Only

68 03 20 Code Trade Name Eagle-Picher Basic Silicate White Lead
5/13/68 Date Chemical Name Basic Silicate White Lead
1 Card No.

Prev. Code

SUPPLIERS (Primary)

CODE

FORMULATING PARAMETERS

1.88 Gal./Cwt. @ 25° C
53.19 Lb./Gal. @ 25° C
100 Wt. % NVM
100 Vol. % NVM
100 Wt. % Pig.
100 Vol. % Pig.

Eagle-Picher Company

202 Basic Silicate White Lead

OTHER CHARACTERISTICS

4. Coeff. of Exp.
TOC Flash
Pt. ° F.
Price/Lb.

Reason for Assignment New

Similar Codes 68 01 00

Advantages Over Similar Material Stain control in redwood and cedar

Codes Which May Become Overstock

HANDLING

Shipping Containers 50 lb. bags
Safety Label Codes No
Safety Precautions Contains Lead. Avoid breathing dust. Wash hands after handling.
Protect from Freezing No
Protect from Moisture No
Flammable Material No
Explosive Material No
Hazardous Material Yes
Age Limit of Material None

OTHER HANDLING INFORMATION

USES

Product Name Type or Rex A6 W 13
Line Item X Cust. Spec. Exper.

Instructions

1. Fill out as completely as possible. Laboratory requesting assignment must furnish complete information.
2. Enumerate all tests on opposite side in consecutive order.
3. Write special tests or procedures which may be necessary under special characteristics and tests.

0007-SWP-063035

The following test numbers are to be run routinely. 1, 2, 3, 4

Tentative Reference Sample to be sent to Cleveland Tech. Service. Yes No X

Chemist Requesting Assignment H. F. Henion Date 5/13/68

Laboratory Director Approving R. C. Hall Lab. D

Received and Approved in Cleveland By R. L. Collins/E. Gardiner Date 5/27/68



THE SHERWIN-WILLIAMS Co.

GENERAL PURCHASING DEPT.

101 PROSPECT AVE., N.W.

CLEVELAND, OHIO 44101

SPECIFICATION FOR PURCHASED MATERIAL

Material Basic Silicate White Lead

Date 9/1/68 Code 68 03 20

Supersedes Specification

General Description:

Date 5/13/68 Code 68 03 20

White free flowing powder for use as pigment in exterior paints.

CHARACTERISTICS	MIN.	STD.	MAX.	TEST METHOD
1. Color	Equal to	Standard		ASTM D 387
2. Texture	Equal to	Standard		
3. Oil Absorption	16		22	ASTM D 281
4. Residue 325 Mesh			1.0	ASTM D 185
5. Moisture (%)			1.5	ASTM D 280

SPECIAL TESTS AND/OR CHARACTERISTICS:

0007-SWP-063036

PRACTICAL REQUIREMENTS: The material shall remain constant in successive lots or shipments with respect to unspecified characteristics to the extent that the seller warrants that no known changes are to be made in raw materials or processing methods of this material without due notification of the buyer.

Code 68 03 20

INTRA COMPANY CONFIDENTIAL

This Side for S-W and Affiliated Company Personnel Only

68 03 30 Code TRADE NAME Eagle Fisher Basic Silicate White Lead

9/4/68 Date CHEMICAL NAME Basic Silicate White Lead

Card No.

Prev. Code

FORMULATING PARAMETERS

1.58 Gal. Cwt. @ 25° C

53.19 Lb./Gal. @ 25° C

100 Wt. % NVM

100 Vol. % NVM

100 Wt. % Pig.

100 Vol. % Pig.

Eagle Fisher Company

202 Basic Silicate White Lead

OTHER CHARACTERISTICS

Coeff. of Exp.

TOC Flash

Pt. ° F.

Price Lb.

HANDLING

Shipping Containers 50 lb. bags Safety Label Codes No

Age Limit None Protect from Freezing No Protect from Moisture Yes

Flammable Material No Explosive Material No Hazardous Material Yes

SAFETY PRECAUTIONS AND OTHER HANDLING INFORMATION

Contains lead. Avoid breathing dust. Wash hands after handling.

USES

Product Name Type or Rex A6 W 13

Line Item A Customer Specification Experimental

Reason for Assignment or Revision

Similar Codes 68 03 00 Codes Which May Become Overstock

Advantages Over Similar Material Stain control in redwood and cedar

SPECIAL TESTS:

INSTRUCTIONS

1. Fill out as completely as possible. Refer to Routine & Policy Bulletin No. 145.
2. Enumerate all tests on opposite side in consecutive order.

The following test numbers are to be run routinely.

Tentative Reference Sample to be sent to Cleveland Tech. Service. Yes No X

Person Requesting Assignment H. F. Henion Date 9/4/68

Laboratory Coordinator Approving R. C. Yarnall Lab. D

Received and Approved in Cleveland By H. I. C. / E. Gardiner Date 9/24/68