

December 9, 1966
NEW FORMULA

PLAINTIFF'S EXHIBIT

GP-1281

NEWBREEZE, GA., PLANT FORMULA

PATCHING PLASTER BGA - 962

KIND OF PLASTER - Sales Designation: Patching Plaster

TESTING CONSISTENCY - 52 to 54. Average 53

ELASTICITY NUMBER - 3 to 5. Average 4

SETTING TIME - 3 to 5 hours. Average 4 hrs.

<u>FORMULA</u>	<u>BATCH</u>	<u>PERCENT</u>	<u>TON</u>
BGA-39	4200.00 lbs.	68.56	1371.20 lbs.
BGA-51	1800.00 "	29.38	587.66 "
Astbestos 7RF-9	120.00 "	1.96	39.18 "
Retarder	6.00 "	0.10	1.93 "
	6126.00 lbs.	100.00	2000.00 lbs.

REMARKS: Setting time to be changed if different set is requested.

PATENT DATA - None.

JEN:sc

SGP 0017259

December 9, 1966
NEW FORMULA

NEWBURY, GA, PLANT FORMULA

PATCHING PLASTER BGA - 962

KIND OF PLASTER - Sales Designation: Patching Plaster

TESTING CONSISTENCY - 52 to 54. Average 53

PLASTICITY NUMBER - 3 to 5. Average 4

SETTING TIME - 3 to 5 hours. Average 4 hrs.

<u>FORMULA</u>	<u>BATCH</u>	<u>PERCENT</u>	<u>TON</u>
BGA-39	4200.00 lbs.	68.56	1371.20 lbs.
BGA-51	1800.00 "	29.38	387.66 "
Asbestos 7RF-9	120.00 "	1.96	39.18 "
Retarder	<u>6.00 "</u>	<u>0.10</u>	<u>1.98 "</u>
	6126.00 lbs.	100.00	2000.00 lbs.

REMARKS: Setting time to be changed if different set is requested.

PATENT DATA - None.

JEN:sc

SGP 0017260

**BRUNSWICK FORMULA #962
ASBESTOS CONTAINING PRODUCTS**

SGP 0017257

— BRUNSWICK FORMULA # 962
— ASBESTOS CONTAINING PRODUCTS

SGP 0017258