

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY-787 LOT 38253

NET WT/PKG NO. PKG PACK. WGT LOCATION PQ

1620 1 T-931674 1 T-299**STUMP** LUMP 3281TOTAL NET WT. 3294 PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

SW 12,18,80

N34804

23

240

CG 03 CODE KY-787-D PKG.

→ DEC-15 80 38253

EST. WGT. 1090 LBS.

CN2
18

3332

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES KY-787-D (Q)	APPROVED BY EWK 9/22/76 DCG 9/27/76
	RETYPE BY CJH 4/2/80	
	MAKING NOTES	
REMARKS		

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS					-PRESSING-		RECORD				
VAT	240				PRESSLOAD	1ST	2ND	3RD	4TH	5TH	
DATE	12-16				STARTED	9:12					
TIME	12:30P				CAKES USED	32					
RELEASED BY	SIB				WATER ON	8:30					
PRESS	22	23	24	25	HRS. WASHED	4					
NO. OF CAKES	46	46	52	48	OHMS	3000					
PRESS WITH	AGITATION				HRS. WASHED						
WASH TO 2000	OHMS WITH 35-75 F WATER				OHMS						
TEST AFTER 2	HOURS				HRS. WASHED						
LOAD ON 6 CARS					OHMS						
					CAKE CONDITION	6					
					NO. CARS LOADED						
					EXPLAIN LOSSES						

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY RELEASED BY

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 12
LUMP WGT. 3281
RELEASED BY AC.

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

38253

41

85

0.00 *

2.94 +

0.14 -

3.01 +

0.14 -

2.91 +

0.14 -

3.00 +

0.14 -

3.25 +

0.14 -

3.22 +

0.14 -

3.18 +

0.14 -

3.10 +

0.14 -

3.27 +

0.14 -

2.89 +

0.14 -

2.80 +

0.14 -

0.92 +

0.14 -

32.81 *