

TYPICAL PHYSICAL PROPERTIES

Specific Gravity	2.45	—
Moisture Content	2.0	% max. by weight
Nature of Surface Charge	Neutral	—
Magnetite Content	0.3	% max. by weight
Refractive Index	1.54 to 1.56	n_D 25° C.
Oil (DOP) Absorption	300 to 350	lb. per 100 lb.
Surface Area	> 60	sq. m. per g.
Fiber Diameter	0.025	microns
Length/Diameter (Aspect Ratio)	200 avg.	—
Bulking Value	4.9	gal. per 100 lb.
Dry Bulk Density (aerated)	1.0	lb. per cu. ft.

PACKAGING AND AVAILABILITY

Single Package—Weight (3-ply paper bag sealed in polyethylene)	10 lb.
Single Pallet—Weight —Dimensions (full pallets covered by waxed cardboard)	350 lb. approx. 53 in. x 44 in. x 61 in. high
Full Carload (available from King City plant)	52 pallets 18,200 lb.
Full 40-ft. Truckload (available nationwide)	17 pallets 5,950 lb.

"Calidria" asbestos RG-244 is stocked at Union Carbide's shipping locations throughout the United States and is available from several distributors.

A07578