

CG 01 CODE YE-698-D PKG

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

LOT MAY -0.81-E 1430

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS			= PRESSING =	RECORD																			
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES	
242	5-18	1:45-A	2571	2	92	93	54	54	54	54	54	54	54	54	3	3000					6		

SAMPLES
DELIVER TOSAMPLED BY
RELEASED BY

= DRYING =		LUMP: - OK - WET - SALTS - CONTAMINATED	
(EXTRUDED) DRY 10 HRS AT 240 DEG F	(NOT EXTRUDED) DRY 10 HRS AT 240 F		

SAMPLES 1 ENV
DELIVER TO COLOR TEST LABNO CARS PULLED
SAMPLED BY
RELEASED BYNO DRUMS
LUMP WGT17
5641

= GRINDING =		RPM		SCREEN		RPM	
MILL MIKROATOMIZE	SCREEN	MAX. TEMP	DEG F	MAX. TEMP	F		
SET ROOF BLAST - GATE AT "9" FOR	HIGH AIR FLOW						

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

3.92 +
0.12 ✓
3.41 +
0.12 ✓
3.06 +
0.12 ✓
10.03 *

1430
41
16

0.00 *

46.38 +
10.03 +
56.41 *

3.54 +
0.12 ✓
3.71 +
0.12 ✓
3.72 +
0.12 ✓
3.44 +
0.12 ✓
3.75 +
0.12 ✓
3.56 +
0.12 ✓
3.74 +
0.12 ✓
3.65 +
0.12 ✓
3.54 +
0.12 ✓
3.50 +
0.12 ✓
3.50 +
0.12 ✓
3.45 +
0.12 ✓
3.68 +
0.12 ✓
1.28 +
0.12 ✓
46.38 *