

TO: PAT LADNER

MOBIL OIL CORP.

MOBILWAX 2305

PLAINTIFF'S EXHIBIT

BIR-271

PROPERTY	TYPICAL
COLOR, ASTM	2
MELTING POINT °F	176
VISCOSITY @ 210°F SUS	80
OIL CONTENT	4%
FLASH POINT °F	540
NEEDLE PENETRATION	
@ 77°F	27
@ 108°F	95
@ 115°F	130
lb/gal @ 60°F	7.74
lb/gal @ 180°F	6.71
GRAVITY , API	—

AN "OFFICIAL" DATA SHEET WILL FOLLOW SHORTLY
IN THE MAIL.

BIRD 005743