

CODE YE-698-D PKG

LOT MAY -0-81-E 1444

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

PROCESSES APPROVED BY
YE-698-D (S) F.POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS

= PRESSING =

RECORD

VAT	245			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5/30/81			STARTED	2:00 PM				
TIME	11:15 AM			CAKES USED	54				
RELEASED BY	P.N.			WATER ON	4:30 PM				
PRESS	2	92	92	HRS. WASHED	1 1/2				
NO. OF CAKES	54	54	54	OHMS	750				
PRESS WITH AGITATION				HRS. WASHED					
WASH TO 2000 OHMS WITH 35-75 F WATER				OHMS					
TEST AFTER 2 HOURS				HRS. WASHED					
LOAD ON 7 CARS				OHMS					

CAKE CONDITION
NO CARS LOADED 7
EXPLAIN LOSSES

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =

(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS
LUMP WGT 5610

= GRINDING =

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT "9" FOR
HIGH AIR FLOW

RPM SCREEN
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

1444
41
100

3.72 +
0.12 -
3.21 +
0.12 -
3.65 +
0.12 -
3.26 +
0.12 -
3.47 +
0.12 -
3.20 +
0.12 -
3.64 +
0.12 -
3.50 +
0.12 -
3.30 +
0.12 -
3.31 +
0.12 -
3.29 +
0.12 -
2.42 +
0.12 -
38.53 *

18

1

~~441-1-11-11-1~~

444-11-

501-~~1111~~

443-11

1444
41
305

0.00 *

6
1

38.53 +
3.46 +
0.12 -
3.21 +
0.12 -
3.44 +
0.12 -
3.39 +
0.12 -
3.10 +
0.12 -
1.69 +
0.12 -
56.10 *

1