

PACER - Feldspar Division

PACER CORPORATION

Box 311 - Custer, South Dakota - 57730

Telephone 605-673-4419

March 10, 1978

PLAINTIFF'S EXHIBIT

BIR-692

Bird & Son, Inc.
Building Material Group
East Walpole, Mass. 02032

Attention: Mr. C.A. Homan, Research Lab

Dear Mr. Homan:

Confirming our recent telephone conversation, enclosed please find copy of original letter to Mr. Frank Wood covering the Brite-X material.


The typical chemical and physical specifications of the Brite-X material is as follows:

SiO_2	-	45.0 - 60.0%	Bulk Density	-	55.0-65.0 lb.cu.ft.
Al_2O_3	-	20.0 - 30.0%	Refractive Index	-	1.66
Fe_2O_3	-	4.0 - 7.0%	Specific Gravity	-	2.75
Na_2O	-	.5 - 3.0%	Oil Absorption	-	45.0%
K_2O	-	3.0 - 10.0%	PH	-	8.0

I trust this will be of benefit to you and would appreciate hearing from you when your tests are completed.

Sincerely,

PACER CORPORATION



J. Fred Miller
Sales Manager

JFM:jg
cc: Robert L. Cullum
Enclosure

Serving the Ceramic and Glass Industries with Plants in Keystone and Custer, South Dakota

BIRD 012677