

MD-3-A

PACKAGE TICKET

CODE YT858

LOT F2H14

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		<u>20</u>	<u>2302</u>	<u>41</u>

STUMP

TOTAL NET WT. 2302

LUMP WT. 2305

PKG. N-CODE

PROD. SLIPV

DATE

OPERATOR

6/21

292

BLEEDING

PROCESSES

APPROVED BY

YT-858-D (D) EWK 10/15/81

TYPED BY JMH

MAKING NOTES

JOB NAME: 46YT858DFD

INSTRUCTIONS				= PRESSING =	RECORD				
VAT	106			PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	5-26-82			STARTED	2:30				
TIME	1:30 PM			CAKES USED	60				
RELEASED BY	cy			WATER ON	10 PM				
PRESS	32	33	35 M-1	HRS. WASHED	12				
NO. OF CAKES	60	60	60 64	M MHOS	120				
PRESS WITHOUT			AGITATION	HRS. WASHED					
WASH TO 250 M MHOS -			35-75* F WATER	M MHOS					
TEST AFTER 6 HOURS				HRS. WASHED					
LOAD ON 10 CARS FOR 30 SERIES PRESS				M MHOS					
LOAD ON 6 CARS FOR M-1 PRESS				CAKE CONDITION					
DO NOT LOAD BOTTOM 2 ROWS OF CARS				NO CARS LOADED	4-9				
MEMBRANE PRESS SLURRY MUST NOT				EXPLAIN LOSSES					
EXCEED 160*F OR 15 PSI BACK PRESS AT									
THE INLET FEED GAUGE. WATER TEST,									
FILL, WASH & COMPRESS PER OP# P.0081									
SAMPLES 2-19 CAR				SAMPLED BY	401				
DELIVER TO 171				RELEASED BY	FD5				

= DRYING =

DRY 36 HOURS AT 150 F	LUMP: - OK - WET - SALTS - CONTAMINATED
	ADDITIONAL DRYING HOURS REQUIRED
SAMPLES	NO DRUMS 16
DELIVER TO	LUMP WGT 2305
	NO CARS PULLED
	SAMPLED BY
	RELEASED BY

= GRINDING =

MILL 10 HSP 1/8" R.F. SCREEN 3450 RPM	SCREEN	RPM
MAX. TEMP. 140* F	MAX. TEMP.	F
INERT MILL WITH CO2 WHEN GRINDING		
PER OP# D.F.0043		
	EXPLAIN LOSSES	
SAMPLE _____ WITHOUT MIXING _____	DATE MIXED	
SAMPLES 1 ENV & 2 PT CANS _____		
DELIVER TO CTL	SAMPLED BY	
	RELEASED BY	

DUP050047574

14
51
52

14
51
343

1.64 +
0.14 -
1.63 +
0.14 -
1.62 +
0.14 -
1.61 +
0.14 -
1.59 +
0.14 -
1.65 +
0.14 -
1.62 +
0.14 -
1.61 +
0.14 -
1.60 +
0.14 -
1.53 +
0.14 -
1.62 +
0.14 -
1.33 +
0.14 -
7.42 *

17.42 +
1.52 +
0.14 -
1.52 +
0.14 -
1.61 +
0.14 -
1.40 +
0.14 -
23.35 *