MAR 8 10 03 AM '40

To Anis

FROM ANIS 9.50

WIEGAND 3-8 9.53 EK

YOUR MEMO FEB 15 SHOWS SOFT POINT ON 2565 LOT M-5 TO BE 74.3 DEGREES ASTM WHICH IS OUR OF SPECIFICATION GIVEN AS 66 TO 72 DEGREES HOWEVER THE BARRETT VALUE OF 78.1 IS WITHIN SPECIFICATION OPERATOR IS FINISHING BATCH AND FINDS M-5 DROPS AT 74 ASTM BUT DOES NOT KNOW WHETHER TO MATCH ASTM SPECIFICATION OR STANDARD M-5 PLS ADVISE BY WIRE WHICH YOU WOULD RECOMMED

GERBER

LAST WD RECOMMEND

PLS RUSH MSG THEY ARE WAITING FOR ANSWER

DSW 331100

STLCOPCB4077744