PLAINTIFF'S EXHIBIT WV-05825

PLAINTIFF'S EXHIBIT 14089.00

11/28/61

006323

NIMA

RECOMMENDED PRACTICE

DEFINITIONS APPLICABLE TO THERMAL INSULATING MATERIALS

COMPOSITIONS

1. Mineral Fiber: A generic term for all non-metallic inorganic fibers. These fibers may be natural, such as asbestos, or may be manufactured, such as rock, slag or glass.

2. 85% Magnesia thermal insulation is composed principally of basic magnesium carbonate with reinforcing mineral fiber.

3. Diatomaceous Silica thermal insulation is composed principapply of diatomaceous earth with or without heat-resistant inorganic binder(s) and reinforcing mineral fiber.

4. Calcium Silicate thermal insulation is composed principally of hydrous calcium silicate with reinforcing mineral fiber.

5. Cellular Glass thermal insulation is composed of glass processed by fusion, ~~converting~~ to form a homogeneous rigid mass of hermetically sealed cells.

6. Amosite Asbestos thermal insulation is composed principally of amosite asbestos fiber with or without heat resistant inorganic binder and filler.

7. Mineral Fiber thermal insulation is composed principally of fibers manufactured from mineral substances such as rock, slag or glass. with or without binder

8. Cellular Plastic thermal insulation is composed of organic materials ~~which are formed into~~ processed to form a homogeneous mass of cells.

FORMS

1. Pipe insulation is thermal insulation suited for application to cylindrical surfaces of pipe and tubing.

   (a) Molded-type Pipe Insulation is thermal insulation preformed in cylindrical, semi-cylindrical or segmented sections to fit pipe and tubing.

   (b) Blanket-type Pipe Insulation is flexible thermal insulation furnished flat in sizes to fit around pipe and tubing.

MC 421724 B 0008

2. Block or Board Insulation is rigid thermal insulation preformed in rectangular units to fit flat or curved surfaces.

3. Insulating Cement is composed of a dry mixture of fibrous, powdery or granular materials which when mixed with water, applied as a plastic mass and dried in place, forms a monolithic thermal insulation.

4. Finishing Cement is composed of a dry mixture of fibrous, powdery or granular materials, which when mixed with water and applied as a plastic mass to thermal insulation, dries to a smooth, hard, protective surface.

5. Insulating-Finishing Cement is a dry mixture of fibrous, powdery or granular materials which when mixed with water, applied as a plastic mass, dires to form a monolithic thermal insulation with a smooth, firm surface.

6. Loose Fill Insulation is thermal insulation composed of a dry mixture of fibrous, powdery, or granular materials for installation between confining surfaces or as a top layer.

7. Blanket Insulation is flexible thermal insulation that can readily be conformed to curved surfaces, and which is suitably bound together to provide units of substantial area for handling and application and which may be faced or reinforced with confining media.

8. Felt Insulation is semi-rigid or flexible thermal insulation composed of mineral fibers with or without binder, (normally furnished in flat sheets.)