

DE NAME: ARMSTRONG QUICK-DRY ENAMEL
 EGORY: INTERIOR ENAMEL
 OR: WHITE
 BER: 836
 LITY FIRST

BS.	GALS.				
				30%	
ment					
227	7.03	Titanium Dioxide		1475	33.483
40	1.52	" Calcium		0575	2.300
50	1.4	Lithopone		045	2.250
icle				70%	
57.5	81.83	Varnish		696	56.954
93	15	Naphtha VM&P		09	1.350
15	2	Cobalt Drier		1.671	3.342
1.05	.125	Lead Drier		834	.104
.7	12 fl. oz.	Anti-skinning Agent		0527	.632
34.25	108.91				100.415
	4.35	- 4% Mfg. Loss			
	104.5	Material Cost per Gallon	-		.961
		Direct Labor Cost	-		.042
		Factory Overhead	-		.067
		Bulk Cost per Gallon	-		1.07
		Complete Package Cost	-		.108
		Factory Cost in Package per Gallon	-		1.178

N 4885