

INTER-OFFICE MEMO **TEARCO CHEMICALS, INC.**

TO A. Stasenko AT Burl. Compound DATE September 23, 1969  
 FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr  
 SUBJECT Firestone 250 Resin W. C. Champion  
 H. H. Duhamel  
 P. Gawason  
 P. R. Scarito  
 D. H. Weintraub  
 File

The results of Firestone 250 resin received on 9/20/69, are as follows:

| Properties | Truck #285 | Truck #99 | Truck #141 | Truck #99 | Burl. 250-12 Spec. |
|------------|------------|-----------|------------|-----------|--------------------|
| Rel. Visc. | 2.46       | 2.45      | 2.50       | 2.47      | 2.40-2.48          |
| Gels       | 9          | 11        | 9          | 8         | 12 Maximum         |
| Dry Blend  | 7.2        | 6.7       | 7.0        | 6.8       | 6.0-8.0            |
| Screen     |            |           |            |           |                    |
| +40        | Tr         | Tr        | Tr         | Tr        | -                  |
| +60        | Tr         | Tr        | Tr         | Tr        | 0-3                |
| +80        | 6          | 31        | 14         | 18        | -                  |
| +100       | 35         | 74        | 67         | 65        | 50-80              |
| +140       | 62         | 92        | 91         | 90        | -                  |
| +200       | 78         | 100       | 99         | 99        | -                  |
| Thru       | 22         | -         | 1          | 1         | 0-5                |

*E. L. Kanyok*  
 E. L. Kanyok

LL/rjl

COLORITE 015872