

CO 03 CODE KY-787-D PKG.

JAN -4 33624

EST. WGT.

2230 LBS.

1980

PROCESSES

KY-787-D (S)

APPROVED BY

EWK 10-19-77

Alternate

DCG 10-25-77

TYPED BY

JIC 11-4-77

MAKING NOTES

REMARKS

TOTAL WGT

7230 6980
(REQ)

NAME: KROLOR® YELLOW-MEDIUM

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

/AT	262				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	1-2-80				STARTED	1201A				
TIME	9:00PM				CAKES USED	34				
RELEASED BY	C.M.				WATER ON	6PM				
PRESS	96	96	95		HRS. WASHED	6				
NO. OF CAKES	10	72	84		OHMS	3500				
PRESS WITH		AGITATION			HRS. WASHED					
WASH TO	2000	OHMS WITH 35-75°F WATER			OHMS					
TEST AFTER	4	HOURS			HRS. WASHED					
LOAD ON 10 CARS					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	13				
					EXPLAIN LOSSES					

SAMPLES 1-8 oz. JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY #382 RELEASED BY

-DRYING-

DRYING DRY 12 HRS AT 220°F.
TEMP. THEN DRY 8 HRS AT 160°F

LUMP: - OK - WET - SALTS - CONTAMINATED

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNo. Drums 33
LUMP WGT. 7163
RELEASED BY BIL

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150°FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE A WITHOUT MIXING

DATE MIXED

SAMPLES 1 env + 1 Pt. Can

DELIVER TO CTL

SAMPLED BY

RELEASED BY

33624
124
41

33624
124
41

33-DRUMS

7

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE KY 795 LOT 33670

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
<u>50</u>	<u>93</u>	<u>4650</u>		

STUMP

TOTAL NET WT. 4650 PKG. N-CODE 1128

PROD. SPVR. SAH DATE 1/12/80 WHSE. OPER. _____