

Name (Trade) **Straight Old Dutch Process** Card No. **1**

Replaces Card No.

Name (Chemical)	Dry White Lead		SIMILAR MATERIALS	
Material (Class)	Pigment		18	
Usage	Paint		BW103	Pulp
Approximate Price		Date	1031	
Bulk	1.74	Gal / 100 lbs. Wt / Gal	67.48	@ 7

ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)				
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method
Color				421.2	Res 325		0.2%	1%	410
				or 421.1	Strength				422.2
Texture					Lead Carbonate	65%		75%	706
					Moisture and			2%	407.3
					Impurities			9	419.2
					Oil Abs.	7			

0007-SWP-063026

SUPPLIER'S NAME	SUPPLIER'S CODE No.
Ozark Smelting National Lead	O.D.P. White Lead O.D.P. " "
Specification: Issued on 6-1-32 Standard Sample Established 12-6-27 Assignment Requested by	
REMARKS:	

X167 5-45 3620

0007-SWP-063027

RAW MATERIAL CHARACTERISTICS AND TESTING										
Experimental No.		Sample Report		Date		12-10-45		No. 1140E		
Name (Trade) Eagle Picher O.D.P.				Card No. 1		Replaces Card No.				
Name (Chemical) White Lead						SIMILAR MATERIALS				
Material (Class) Pigment						18				
Usage Paint						BW 102		Pulp		
Approximate Price						1031				
Bulk 1.74 Gal./100 lbs. Wt./Gal. 57.48 @						T				
ROUTINE TESTS (Must be Run on Each Shipment)					SECONDARY TESTS (Run Different One Each Shipment)					
TEST	Min.	Stan.	Max.	Method	TEST	Min.	Stan.	Max.	Method	
Color				421.2	Res 325			0.2%	1%	410
				or 421.1	Strength					422.2
Texture					Lead Carbonate	65%		75%		706
					Moisture and			2%		407.1
					Impurities					
					Oil Abs.	9		13.6		419.2

0007-SWP-063028

SUPPLIER'S NAME

SUPPLIER'S CODE No.

Eagle Picher Co.

Basic Carbonate White Lead "A"

Specification: Issued on 6-1-32

Standard Sample Established

12-6-27

Assignment Requested by

REMARKS:

X157 5-45 3620

0007-SWP-063029