MD-3-A

PACKAGE TICKET

CODE BT297 LOT K2K80

PO	NET WT/PKG.	NO. PKG.	PACK WT.	LOCATION
		17	2478	60
	STUMP			

TOTAL NET WT. 2478

LUMP WT. 2454 PKG. N-CODE

PROD. SUPV. DATE 10 22 OPERATOR 292

DUP050103658

0·C

1·36 +
1·49 +
1·52 +
1·58 +
1·42 +
1·55 +
1·46 +
1·38 +
1·51 +
1·43 +
1·59 +
1·48 +
1·80 +
1·57 +
1·47 +
1·64 +
0·53 +

017

24·78 ↳

DUP050103659

PRODUCT NAME = MONASTRAL BLUE G

DATE PRINTED: 12/07/81

CG 20 CODE BT-297-D PKG ___

PROCESSES BT-297-D (M) | APPROVED BY BBK 11/24/81

TYPED BY: JMH

OCT 18 1982 (DATE) K2K80 (LOT)

20-21 Tens

NOTES:

TOTAL EST'D WGT = 2325 LBS

17

JOB NAME: 20BT297DPM

= PRESSING =

INSTRUCTIONS						RECORD	1ST	2ND	3RD	4TH	5TH
VAT						PRESSLOAD					
DATE						STARTED	30				
TIME						CAKES USED	88				
RELEASED BY						WATER ON					
PRESS	15+16	17+18				HRS. WASHED					
NO.OF CAKES	6X42	6X42				OHMS					
PRESS WITHOUT AGITATION						HRS. WASHED					
WASH TO ----- OHMS -						OHMS					
TEST AFTER -- HOURS						HRS. WASHED					
LOAD ON 6 CARS						OHMS					
						CAKE CONDITION					
						NO CARS LOADED	5+5				
						EXPLAIN LOSSES					

SAMPLES JAR

DELIVER TO

SAMPLED BY

RELEASED BY SJL

= DRYING =

DRY 16 HOURS AT 220*F

LUMP: - OK - WET - SALTS - CONTAMINATD

colors appeared dry

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 16

LUMP WGT 2484

SAMPLES

DELIVER TO

NO CARS PULLED

SAMPLED BY

RELEASED BY A.R

= GRINDING =

MILL 7 OR 8LSP 3/32"RP SCREN 1785RPM

MAX. TEMP 140 DEG F

Inert mill with CO_2 when grinding per OPH OF 0043

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV.

DELIVER TO CTL

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

DATE MIXED 10-22-82

SAMPLED BY 177

RELEASED BY O. Neeman

DUP050103660

8
124
51

1.64 +
0.14
1.56 +
0.14
1.66 +
0.14
1.55 +
0.14
1.51 +
0.14
1.57 +
0.14
0.77 +
0.14
9.28 *

0.00 *

80
51
225

0.00 *

9.28 +
1.66 +
0.14
2.04 +
0.14
1.96 +
0.14
1.76 +
0.14
1.75 +
0.14
1.80 +
0.14
1.86 +
0.14
1.94 +
0.14
2.05 +
0.14
24.84 *

DUP050103661