

St. Louis Sales

July 26, 1957

St. Louis Sales

Mr. H. D. Ohm

ACOUSTICAL PLASTER FOR
MACHINE APPLICATION

T. J. Dalton - dk

CC: Mr. M. C. Hoven - General Sales
Mr. C. E. Abbey - General Sales
Mr. C. G. Shuttlesworth - Paoli Lab.
Mr. O. P. Grieve - Paoli Lab.
Mr. J. R. Watt - Paoli Lab.
Mr. Myron Read - Fort Dodge Plant

Re: M 17 School
George Robertson Plastering Co.

A few small ceilings were applied last week, first coat 1/2" thick with the hawk-trowel and sprayed the finish coat on this week with the small E-Z On (cuplike) gun. The first coat applied with the tools worked fine, just as well as any other brand and the plasterers like it. The finish coat also worked perfectly and makes a good job. The few small fissures in the first coat were nil and closed with the sweep of a trowel.

I could say nothing wrong about this product except that we still get small lump at times in the finish and when put through a 3/8" screen you can readily see them. I do not feel that this is serious but feel that the laboratory has the solution to remedy same.

If I can pass on any further information I'll be glad to do so.

RECEIVED
PAOLI, PENNSYLVANIA

JUL 31 1957

CERTAIN-TEED PRODUCTS
CORPORATION