

FILE NAME: Phenolic Resins (PHR)

DATE: 1977

DOC#: PHR058

DOCUMENT DESCRIPTION: Product Specifications, Owens-Corning Fiberglas - Duct System, Asbestos on Ingredient List; from O-C File



PROCESS SPECIFICATION
QUALITY CONTROL & SPECIFICATION DEPARTMENT

Produced in Canada under seal by order of
Judge Paul Riley and Gordon Meag.
October 16, 1989. In JARVIS v. A. J. Green
et al. 87-11230

PRODUCT: 935 MA DUCT SYSTEM MASTIC, TYPE II (X-694)

A. FORMULATION

Ingredients listed in the order of addition.

INGREDIENT	P.A.S.	CHARGE WEIGHT	CHARGE VOLUME
Triple-Blend Solvent*	CRM.59.1.714	2490 lbs.	382 gal.
Parcill 170 HV (85%)	.538	238 lbs.	20 1/2 gal.
Thixcin GR	.661	46 1/2 lbs.	
Water			
Phenolic Resin CKM-1634	.531	225 lbs.	
Titanox RA-50	.472	200 lbs.	
Oncor 23 A	.537	43 lbs.	
MgO Maglite D	.534	33 lbs.	
ZnO Kadox 15	.380	33 lbs.	
Zalba Special	.539	9 lbs.	
Asbestos Chrysolite Shorts 6-D1	3.273	210 lbs.	
Hydral 710	.533	110 lbs.	

Pre-React for 30 minutes.

Neoprene W CRM.59.1.536 425 lbs. (7 bags + 40 lbs)
* Triple-Blend: Toluene, Lacolene, Hexasol - 6.52 lbs./gal.

B. SAFETY - GENERAL

Operator must wear an air mask and protective clothing when charging the Asbestos
Safety glasses must be worn at all times. Triple-Blend solvent is flammable. Keep
all sources of ignition away from the area while charging and mixing the batch.

C. MIXING PROCEDURE

1. Add ingredients to churn in the order listed.

2. Start agitator.

Proprietary: Information herein is the property of Owens-Corning Fiberglas Corporation and is not
to be disclosed by the recipient to others without the written consent of Owens-Corning. This docu-
ment may not be copied nor reproduced and must be returned to Owens-Corning upon request.

INQUIRES REGARDING THIS SPECIFICATION SHOULD BE FORWARDED TO THE OFFICE OF ISSUANCE.

PLAINTIFF'S
EXHIBIT

4309.0

p. 1 of 1

42 013 1831