

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

Y5698

LOT

G-1124

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PQ

2856

1

T-139

2574

1

T-229

LUMP
STUMP

5240

TOTAL NET WT.

5420

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

WJK

7/11/

3 PRODUCT NAME = MOLYBDATE ORANGE

WCG 01 CODE YE-698-D PKG

LOT JUN 20 1981

G1124

EST'D WGT 5632

TOTAL EST'D WGT= LBS (CRT ENTRY)

NON-BLEEDING

PROCESSES APPROVED BY
YE-698-D (S) F. POST 4/14/81
ALTERNATE
TYPED BY JMH

MAKING NOTES

JOB NAME: 01YE698DPS

INSTRUCTIONS			= PRESSING =	RECORD																		
VAT	DATE	TIME	RELEASED BY	PRESS	NO. OF CAKES	PRESS WITH AGITATION	WASH TO 2000 OHMS WITH 35-75 F WATER	TEST AFTER 2 HOURS	LOAD ON 7 CARS	PRESSLOAD	STARTED	CAKES USED	WATER ON	HRS. WASHED	OHMS	HRS. WASHED	OHMS	HRS. WASHED	OHMS	CAKE CONDITION	NO CARS LOADED	EXPLAIN LOSSES
245	7/3/81	12:50 PM	R.H.	2	92	93	54	54	54	181	2ND	54	98	4	1000					6		

SAMPLES
DELIVER TO

SAMPLED BY
RELEASED BY

= DRYING =
(EXTRUDED) DRY 10 HRS AT 240 DEG F
(NOT EXTRUDED) DRY 10 HRS AT 240 F

LUMP: - OK - WET - SALTS - CONTAMINATED

No record of any processing

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES 1 ENV
DELIVER TO COLOR TEST LAB

NO CARS PULLED
SAMPLED BY
RELEASED BY

NO DRUMS 17
LUMP WGT 5240

MILL MIKROATOMIZE SCREEN
MAX. TEMP DEG F
SET ROOF BLAST - GATE AT '9' FOR
HIGH AIR FLOW

= GRINDING =
RPM SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES
DELIVER TO CTL

DATE MIXED
SAMPLED BY
RELEASED BY

1124
41
324

0.00 *

3.07 +

0.14 -

3.49 +

0.14 -

3.15 +

0.14 -

3.15 +

0.14 -

2.93 +

0.14 -

2.90 +

0.14 -

3.20 +

0.14 -

3.09 +

0.14 -

3.38 +

0.14 -

3.45 +

0.14 -

3.16 +

0.14 -

3.03 +

0.14 -

3.38 +

0.14 -

3.37 +

0.14 -

3.07 +

0.14 -

3.21 +

0.14 -

3.75 +

0.14 -

52.40 *

17