

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE GP501 LOT 36960

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
------------	---------	-----------	----------	----

	<u>5</u>	<u>1000</u>	<u>41</u>	

STUMP Lump wt 1002

TOTAL NET WT. 1000 PKG. N-CODE _____

PROD. SPVR. _____ DATE _____ WHSE. OPER. _____

995 9 24 292

N37397

D.T

201.+

195.+

200.+

213.+

191.+

1000.T

CG 18 CODE GP-501-D PKG. _____

→ AUG-28-80 36960

EST. WGT. 0 ~~3352~~ LBS.SPLIT OFF: 1002# FROM GP501-D LOT 36693
UNFIRED PORTION FROM FIRED CARS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES
GP-501-D (P) APPROVED BY
EWK 03-17-75
DCG 03-17-75

TYPED BY

emw062979

MAKING NOTES

REMARKS

NAME: RAMAPO® GREEN B

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT						PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE						STARTED					
TIME						CAKES USED					
RELEASED BY						WATER ON					
PRESS	12	20	21	26		HRS. WASHED					
NO. OF CAKES	3 x 36	2 x 42	2 x 42	3 x 40		OHMS					
PRESS	with	AGITATION				HRS. WASHED					
WASH TO	4000	OHMS with 35-75°F water				OHMS					
TEST AFTER	3	HOURS				HRS. WASHED					
LOAD	on 8 cars					OHMS					
						CAKE CONDITION					
						NO. CARS LOADED					
						EXPLAIN LOSSES					

SAMPLES

DELIVER TO

SAMPLED BY

RELEASED BY

-DRYING-

Dry 12 hrs at 180°F

Dry 12 hrs at 140°F

Std & Abrev

Dry P & S

Sides 180 DN

Cool - 100

Use 41 Gal L/P

LUMP: - OK - WET - SALTS - CONTAMINATED

Dryer sections used:

Split off - See above note

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 5

SAMPLES

DELIVER TO

NO. CARS PULLED

SAMPLED BY

LUMP WGT. 1002

RELEASED BY

-GRINDING-

MILL 7 or 8 LSP 3/32" RP SCREEN 1785 RPM

MAX. TEMP. °F

Use 41 Gal L/P

SCREEN

MAX. TEMP. °F

RPM

°F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 Env & 2 Pt Cans

DELIVER TO CTL

DATE MIXED


SAMPLED BY

RELEASED BY

N37397.01

DUP050041881

GP501-D



2.18	+
0.14	-
2.37	+
0.14	-
2.27	+
0.14	-
2.15	+
0.14	-
1.75	+
0.14	-
10.02	*