MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE 110-785 LOT 38165

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
2,000	1	T —	177	
1,998	1	T —	121	
1,916	1	T —	76	
STUMP WOOD			5,914	

TOTAL NET WT. 5,914 PKG. N–CODE

PROD. SPVR. DATE WHSE. OPER.

JT 2/11/10

N34617

DUP050104650

92/247

CG 04 CODE KO-789-D PKG.

→ DEC -5 80 38165

EST. WGT. 1032 LBS.

OK K

PROCESSING INSTRUCTIONS: BATCH UNIT

	PROCESSES	APPROVED BY
	TYPED BY	

MAKING NOTES

REMARKS

TOTAL WGT. 5232#

ME: NON-BLEEDING

INSTRUCTIONS —PRESSING— RECORD

T			247		
TE			12-6-80		
ME			11:45 AM		
ELEASED BY			K.A.		
ESS	22	23	24	25	
. OF CAKES	46	46	52	48	

ESS. WITH
SH TO 5000 OHMS
ST AFTER
AD OF 5 CARS

AGITATION
OHMS WITH 35-75 F WATER
HOURS

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	8				
CAKES USED	52				
WATER ON	2				
HRS. WASHED	3				
OHMS	5000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO. CARS LOADED	5				

EXPLAIN LOSSES

MPLES 1-8 OZ JAR
LIVER TO CTL FOR COLOR

SAMPLED BY RELEASED BY ac.

—DRYING—

RY 16 HOURS AT 220 F

LUMP: -- OK - WET - SALTS - CONTAMINATED

Color appeared OK
Possibly more material added in making
when press was dropped all Frames
were overloaded Released 12-9-80

ADDITIONAL DRYING HOURS REQUIRED

NO. DRUMS 21

PLES
LIVER TO

NO. CARS PULLED LUMP WGT. 5993
SAMPLED BY RELEASED BY ac.

—GRINDING—

L 938 3/32" RP SCREEN 3500 RPM
. TEMP. 210 °F

SCREEN RPM
MAX. TEMP. °F


EXPLAIN LOSSES

LE / WITHOUT MIXING
ES 1 ENV. + 1 PINT CAN
ER TO C T L

DATE MIXED

SAMPLED BY RELEASED BY

DUP050104651



DUP050104652