VISCOSITY WORK SHEET

Item 1458 & 1464 & 1473 & 1476 P.T.No. Date 3-5-54

Worker Polymer Butacite Solvent 2B Alcohol

For Sawyer Charge 1209 Temperature 25°C

Viscometer No. AT Efflux Time 1616 Weight: Gross

Viscometer No. BT Efflux Time 1688 Tare

Viscometer No. 331 / 332 Efflux Time 1796 / 1741 Net 10560

Sample	Flask	Visc. No.	Solution Efflux Times		Rel. Inh. visc. (eps) Visc. or M.W.
4-BAC-82 DRY	615	BT	410.9 411.1 411.1		69.4
	724	AT	424.9 425.0 424.9		68.7
4-BAC-83A DRY	1	332	396.1 395.3 395.6 395.6		68.9
	D	BT	405.5 406.4 405.7		68.4
4-BAC-85 DRY	593	331	399.9 399.5 399.8		70.0
	290	332	399.4 399.6 399.7 399.7		69.6
4-BAC-86 DRY	18	BT	215.1 215.1		36.2
	Tish	331	208.5 203.6 203.6		36.2
4-BAC-87 DRY	621	331	327.0 327.3 327.4 327.6		58.0
	U	AT	368.1 358.2 358.5 358.7 358.7		57.9

PC-1

N38539