MD-3-A

PACKAGE TICKET (DRY AND PASTE ONLY)

CODE KY-908 LOT E-1319

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PO
1800	1	T	71	
1825	1	T-	141	
	Lump			
	STUMP	3631		

TOTAL NET WT. 3625 PKG. N-CODE

PROD. SPVR. DATE WHSE. OPER.

JF 5/12/81

32/22/22

PRODUCT NAME = KROLOR YELLOW-LIGHT

NON-BLEEDING

CG 63 CODE KY-908-D PKG ____

PROCESSES: KY908D(D) ALTERNATE

APPROVED BY: FWP 01/27/81

TYPED BY

LOT MAY -0-81- Ξ1319

EST'D WGT 949 LBS

TOTAL EST'D WGT=~~3549~~ 3599 LBS (CRT ENTRY)

MAKING NOTES

JOB NAME: 03KY908DPD

INSTRUCTIONS = PRESSING = RECORD

VAT	202			
DATE	5-13-81			
TIME	5:45PM			
RELEASED BY	E.M.			
PRESS	2	22	23	24
NO. OF CAKES	46	46	46	52

32

PRESS WITH AGITATION

WASH TO 2000 OHMS - 135-145 F WATER

TEST AFTER 2 HOURS

LOAD ON 6 CARS

SAMPLES 8 OZ JAR

DELIVER TO CTL FOR COLOR

PRESSLOAD	1ST	2ND	3RD	4TH	5TH
STARTED	6PM				
CAKES USED	46				
WATER ON	9PM				
HRS. WASHED	3				
OHMS	2000				
HRS. WASHED					
OHMS					
HRS. WASHED					
OHMS					
CAKE CONDITION					
NO CARS LOADED	6				

EXPLAIN LOSSES

SAMPLED BY

RELEASED BY TDJ

= DRYING =

DRY 24 HOURS AT 180 F

NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES

DELIVER TO

NO DRUMS 13

LUMP WGT 3631

NO CARS PULLED

SAMPLED BY

RELEASED BY

= GRINDING =

MILL 939 HSP 1/8"RP SCREEN 3500 RPM

MAX. TEMP. 170 F

SCREEN RPM

MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING

SAMPLES 1 ENV & 1 PT CAN

DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050096519

1319
124
41

2.91 +
0.14 -/
3.10 +
0.14 -/
2.92 +
0.14 -/
2.97 +
0.14 -/
2.88 +
0.14 -/
2.86 +
0.14 -/
3.00 +
0.14 -/
2.90 +
0.14 -/
3.01 +
0.14 -/
3.06 +
0.14 -/
2.97 +
0.14 -/
3.09 +
0.14 -/
2.48 +
0.14 -/
36.31 *

DUP050096520