

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

T A. Stasenko - **AT** Burl. Compound **DATE** September 12, 1969
FROM E. L. Kanyok ✓ **AT** Burlington **COPY TO** H. B. Carr
SUBJECT Firestone 250 Resin W. C. Champion
H. H. Duhamel
P. Gawason
P. R. Scarito
D. H. Weintraub
File ✓

The results of Firestone 250 resin received on 9/11/69 are as follows:

<u>Properties</u>	<u>Truck #273</u>	<u>Truck #99</u>	<u>Burl. 250-12 Spec.</u>
Relative Viscosity	2.48	2.52	2.40 - 2.48
Gels	10	12	12 Maximum
Dry Blend	6.4	6.7	6.0 - 8.0
Screen			
+40	-	-	-
+60	Tr	Tr	0 - 3
+80	6	7	-
+100	50	51	50 - 80
+140	88	84	-
+200	100	96	-
Thru	-	4	0 - 5.

E. L. Kanyok
E. L. Kanyok

ELK/rjl