

MD 3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

KY-908

LOT

35412

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PG

1846 - 1 - T - 213

1772 - 1 - T - 220

LUMP
STUMP 3665#

TOTAL NET WT.

3618

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JPP

4/25/80

N32238

CG 03 CODE KY-908-D PKG.

APR 17 35412

EST WGT. 949 LBS.

OK
H

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES

KY-908-D (E)

Alternate

APPROVED BY

EWK 12/12/77

DCG 12/14/77

TYPED BY

RJ 2/14/78

MAKING NOTES

REMARKS

Total Wgt. 3549 #

NAME: Krolor® Yellow - Light

NON-BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT	262				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	4-18-80				STARTED	7:15 PM				
TIME	2:30 PM				CAKES USED	42				
RELEASED BY	A. C.				WATER ON	10 PM				
PRESS	2	22	23	24	HRS. WASHED	5				
NO. OF CAKES	46	46	46	52	OHMS	200				
PRESS with	AGITATION				HRS. WASHED					
WASH TO	2000	OHMS with 135-145°F water				OHMS				
TEST AFTER	2	HOURS				HRS. WASHED				
LOAD	on 6 cars				OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	4				
					EXPLAIN LOSSES					

SAMPLES 8oz Jar
DELIVER TO Ctl for color

SAMPLED BY

RELEASED BY

-DRYING-

DRY 24 HOURS AT 180 °F LUMP: - OK - WET - SALTS - CONTAMINATED

Dry on first stage only.

Color appears to be dry

Reset every 5 hrs til dry.

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED
SAMPLED BYNO. DRUMS 12
LUMP WGT. 3665
RELEASED BY

-GRINDING-

MILL 939 HSP 1/8" RP	SCREEN 3500 RPM	SCREEN	RPM
MAX. TEMP. 170 °F		MAX. TEMP.	°F
		EXPLAIN LOSSES	
SAMPLE / WITHOUT MIXING		DATE MIXED	
SAMPLES 1 ENV & 1 PT CAN		SAMPLED BY	RELEASED BY
DELIVER TO C T L			

N32238.01

DUP050457224

354.12 N C
.41 N
2.52 N
.00 T

3.33 C
.14 -
3.43
.14 -
3.27
.14 -
3.40
.14 -
3.26
.14 -
3.24
.14 -
3.34
.14 -
3.41
.14 -
3.30
.14 -
3.24
.14 -
3.24
.14 -
1.87
.14 -
36.65 T

N32238.02

DUP050457225