

MD-3-A

PACKAGE TICKET

(DRY AND PASTE ONLY)

CODE

K4-787

LOT

37929

NET WT/PKG

NO. PKG

PACK. WGT

LOCATION

PO

1660

1

T-224

1650

1

T-84

TOTAL NET WT.

3310

PKG. N-CODE

PROD. SPVR.

DATE

WHSE. OPER.

JMM

11/21/80

N34854

23/244
CG 03 CODE KY-787-D PKG. _____
→ NOV-17 80 37929
EST. WGT. 1000 LBS.

PROCESSING INSTRUCTIONS: BATCH UNIT

PROCESSES	APPROVED BY
KY-787-D (Q)	EWK 9/22/76
	DCG 9/27/76
RETYPE BY	
CJH 4/2/80	

MAKING NOTES

REMARKS

TOTAL WGT. 3332 #

NAME: KROLOR - YELLOW MEDIUM

NON-BLEEDING

INSTRUCTIONS					-PRESSING-	RECORD				
YAT	244				PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE	11-18				STARTED	6AM				
TIME	5:45 AM				CAKES USED	46				
RELEASED BY	OK				WATER ON	11:30				
PRESS	22	23	24	25	HRS. WASHED	3				
NO. OF CAKES	46	46	52	48	OHMS	3500				
PRESS WITH AGITATION					HRS. WASHED					
WASH TO 2000 OHMS WITH 35-75 F WATER					OHMS					
TEST AFTER 2 HOURS					HRS. WASHED					
LOAD ON 6 CARS					OHMS					
					CAKE CONDITION					
					NO. CARS LOADED	6				
					EXPLAIN LOSSES					

SAMPLES 1-8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY 401 RELEASED BY J.K.

-DRYING-

DRY 12 HRS AT 220 °F
THEN DRY 6 HRS AT 160 °F

LUMP: - OK - WET - SALTS - CONTAMINATE

ADDITIONAL DRYING HOURS REQUIRED

SAMPLES
DELIVER TONO. CARS PULLED 6
SAMPLED BY

NO. DRUMS 12

LUMP WGT. 3311

RELEASED BY B.H.

-GRINDING-

MILL 939 HSP 3/32" RP SCREEN 3500 RPM
MAX. TEMP. 150 °FSCREEN RPM
MAX. TEMP. °F

EXPLAIN LOSSES

SAMPLE AFTER / WITHOUT MIXING
SAMPLES 1 ENV & 1 PT. CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY

RELEASED BY

DUP050105558

329

313

293

305

304

305

300

294

312

308

285

107

37229

41

231

0

329

12

313

12

293

12

305

12

304

12

305

12

300

12

294

12

312

12

306

12

235

12

107

12

311