

MEMBER CG 46 CODE YC-11-A PKG.

→ NOV-26 80 38053

EST. WGT. 2238 LBS.

PROCESSES	APPROVED BY
(D) YC-11-A	EWK 9-28-76
	BBK 10-17-77
	DCG 11-29-77
TYPED BY	
JLC 12-8-77	
MAKING NOTES	

REMARKS

NAME: DALAMAR® YELLOW

BLEEDING

INSTRUCTIONS

-PRESSING-

RECORD

VAT				105	PRESSLOAD	1ST	2ND	3RD	4TH	5TH
DATE				11-26-80	STARTED	7:50 AM				
TIME				6:10 PM	CAKES USED	62				
RELEASED BY				M. J. SW	WATER ON	8:45 AM				
PRESS	32	33	35	M. J. SW	HRS. WASHED	4				
NO. OF CAKES	60	62	60		OHMS	5000				
PRESS	WITHOUT AGITATION				HRS. WASHED					
WASH TO	4000 OHMS WITH 35-75°F WATER				OHMS					
TEST AFTER	4 HOURS				HRS. WASHED					
LOAD	IN METAL DRUMS AT 325# NET PER DRUM				OHMS					
AIR BLOW PRESSCAKE 15 MIN AT 40PSI					CAKE CONDITION					
					NO. CARS LOADED					
					EXPLAIN LOSSES					

SAMPLES THIEF SAMPLE & FILL 1-8 oz. jar
DELIVER TO CTL for color

SAMPLED BY

RELEASED BY

-DRYING-

DRY	HOURS AT	OF	LUMP: - OK - WET - SALTS - CONTAMINATED
DO NOT DRY			
			ADDITIONAL DRYING HOURS REQUIRED
			NO. DRUMS
SAMPLES			NO. CARS PULLED
DELIVER TO			LUMP WGT.
			RELEASED BY

-GRINDING-

MILL	SCREEN	RPM	SCREEN	RPM
MAX. TEMP.	°F		MAX. TEMP.	°F
			EXPLAIN LOSSES	
SAMPLE AFTER / WITHOUT MIXING			DATE MIXED	
SAMPLES				
DELIVER TO CTL			SAMPLED BY	
			RELEASED BY	

N35279