

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko At Burl. Compound DATE September 24, 1969

FROM E. L. Kanyok ✓ At Burlington COPY TO H. B. Carr

SUBJECT Union Carbide 250 Resin R. S. Cole

W. C. Champion

H. H. Duhamel

P. Gawason

P. R. Scarito

D. H. Weintraub

File

The results of Union Carbide 250 resin received on 9/23/69 are as follows:

<u>Properties</u>	<u>Truck #285</u>	<u>Truck #87</u>	<u>Burl. 250-12 Spec.</u>
Rel. Visc.	2.58 Resample 2.58	2.51	2.40 - 2.48
Gels	Approx. 80 Resample 85	19	12 Maximum
Dry Blend	5.0	4.9	6.0 - 8.0
Screen			
+40	-	-	-
+60	Tr	Tr	0 - 3
+80	6	9	-
+100	52	61	50 - 80
+140	87	92	-
+200	96	98	-
Thru	4	2	0 - 5

Relative viscosity and gels on truck #285 are well above our spec. ~~This truck shipment was sent back to the supplier.~~

THIS RESIN SHOULD BE MONITORED BY THE Compound Plant FOR QUALITY OF THE SAID PRODUCT

E. L. Kanyok
E. L. Kanyok

ELK/rjl

COLORITE 015868