CODE KP408 LOT E1020

NET WT/PKG	NO. PKG	PACK. WGT	LOCATION	PQ
1890	1	T	141	
1630	1	T	280	
	STUMP	3593#		

TOTAL NET WT. 3,520 PKG. N–CODE

PROD. SPVR.	DATE	WHSE. OPER.
[signature]	5-5-81	

32/262

CG 03 CODE KY-908-D PKG ____

LOT MAY -0-81- Σ1020

EST'D WGT 1~~600~~ LBS

TOTAL EST'D WGT=~~6303~~ 3549 LBS (CRT ENTRY)

012/KP

PROCEDURES APPROVED BY
KY908D(F) FWP 01/~~27~~/81
ALTERNATE
TYPED BY WRT/JMW

MAKING NOTES _____

JOB NAME: 03KY908DPF

= PRESSING =

INSTRUCTIONS					RECORD	1ST	2ND	3RD	4TH	5TH
VAT	262				PRESSLOAD					
DATE	4-29-81				STARTED	9 Am				
TIME	9:00 AM				CAKES USED	32				
RELEASED BY	[illegible]				WATER ON	11:30 Am				
PRESS	96	95	32		HRS. WASHED	8				
NO.OF CAKES	72	72			OHMS	2000				
PRESS WITH		AGITATION			HRS. WASHED					
WASH TO 2000 OHMS - 135-145 F WATER					OHMS					
TEST AFTER 3 HOURS					HRS. WASHED					
LOAD ON ~~10~~ 6 CARS					OHMS					
					CAKE CONDITION					
					NO CARS LOADED					
					EXPLAIN LOSSES	6				

SAMPLES 8 OZ JAR
DELIVER TO CTL FOR COLOR

SAMPLED BY
RELEASED BY

= DRYING =

DRY 24 HOURS AT 180 F
NOTE: DRY ON FIRST STAGE ONLY.
RE-SET ON FIRST STAGE TIL DRY.

LUMP: - OK - WET - SALTS - CONTAMINATD

ADDITIONAL DRYING HOURS REQUIRED

NO DRUMS 13
LUMP WGT 3592

SAMPLES
DELIVER TO

NO CARS PULLED
SAMPLED BY
RELEASED BY

= GRINDING =

MILL 939 HSP 1/8"RP SCREEN 3500 RPM
MAX. TEMP. 170 F

SCREEN RPM
MAX. TEMP. F

EXPLAIN LOSSES

SAMPLE WITHOUT MIXING
SAMPLES 1 ENV & 1 PT CAN
DELIVER TO CTL

DATE MIXED

SAMPLED BY
RELEASED BY

DUP050096267

1020
41
17

0.00 *

3.31 +
0.12 -/
3.05 +
0.12 -/
3.11 +
0.12 -/
3.30 +
0.12 -/
3.19 +
0.12 -/
3.11 +
0.12 -/
2.93 +
0.12 -/
1.76 +
0.12 -/
22.80 *

1020
41
305

0.00 *

22.80 +
2.88 +
0.12 -/
2.72 +
0.12 -/
2.87 +
0.12 -/
2.82 +
0.12 -/
2.43 +
0.12 -/
35.92 *

DUP050096268