



E. I. DU PONT DE NEMOURS & COMPANY
INCORPORATED

ORGANIC CHEMICALS DEPARTMENT
TECHNICAL LABORATORY

CC: C. H. Asbury, Orchem, Wilm.
D. F. Harkins, Orchem, Wilm.
R. O. Kettner, Adm. Bldg.
H. I. Stryker, Adm. Bldg.
J. T. Hale, D&C Bldg.
M. D. Carter, D&C Bldg.
W. J. Clem, "Ponsol" Lab.
Shipping House

May 10, 1963

Mr. R. L. Burnett, Manager
Lakes and Leather Section
Dyes and Chemicals Division

"LITHOSOL" FAST VIOLET 4RNL PASTE
LOT 109 - 11,239 LB.

This lot of "Lithosol" Fast Violet 4RNL Paste has been classified as "dump and hold" material, as discussed with Mr. W. C. Cuntz, because of deficient shade and tinctorial strength when tested on paint panels against Standard Lot 108.

A comparison of the ammonium resinated toners in paint tests shows the following comparisons:

<u>Parts</u>	<u>Sample</u>	<u>Shade</u>	<u>Solvent Bleed</u>
100	Lot 108	Std.	Std.
115	Lot 109	1R,3D	3 Inferior

C. A. Bamberger
C. A. Bamberger

CAB/aml