

INTER-OFFICE MEMO **TENNECO CHEMICALS, INC.**

TO A. Stasenko - AT Burl. Compound DATE August 27, 1969

FROM E. L. Kanyok AT Burlington COPY TO H. B. Carr

SUBJECT Firestone 225 Resin P. H. Duhamel

P. Gawason

P. R. Scarito

File ✓

The results of Firestone 225 resin, lot no. P-9570 and P-9571, received on 8/26/69 are as follows:

<u>Properties</u>	<u>P-9570</u>	<u>P-9571</u>	<u>Burl. 225 Spec.</u>
Relative Viscosity	2.28	2.30	2.26 - 2.33
Gels	9	11	13 maximum
Dry Blend	6.1	6.3	6.0 - 8.0
Screen			
+40	Tr	-	-
+60	1	1	0 - Tr
+80	32	31	-
+100	68	68	40 - 70
+140	93	92	-
+200	100	97	-
Thru	-	3	0 - 5

E. L. Kanyok
E. L. Kanyok

ELK/rjl