



KODARAS ACOUSTICAL LABORATORIES

DIVISION OF MICHAEL J. KODARAS, INC.

75-02 51st AVENUE/ELMHURST, NEW YORK 11373/TELEPHONE 212-446-1550



July 17th, 1967


Sprayed Mineral Fiber Manufacturers Association, Inc.
c/o Mr. H. L. Levine
Asbestospray Corporation
1060 Broad Street
Newark, New Jersey 07102

Dear Bert:

In accordance with the SMFMA letter of July 3rd, 1967, signed by H. L. Levine, we have proceeded to test erosion of sample #1 at an air velocity of 2000'/min. As you know, this sample has been run at 800' velocity for a total period (including purge) of 48 hours.

The 2000'/min. test was conducted exactly as described in our report dated July 10th, 1967. The results were as follows:

	<u>Net Gain</u> <u>SF/Gr.</u>
3 hours - 2010 fpm	.009 (.01)
3 hours - 2006 fpm	.009 (.01)
18 hours - 2002 fpm	.009 (.01)
24 hours - 2006 fpm	.009 (.01)



Please advise if you wish any further tests conducted in this series.

Yours sincerely,

KODARAS ACOUSTICAL LABORATORIES
MICHAEL J. KODARAS, INC.

Michael J. Kodaras
President

MJK:sl

cc: Mr. Harry Wilson
Dr. Morris Lief
Mr. Frank Stumpf