



PRODUCT DATA

PLAINTIFF'S

EXHIBIT NO. 8-23
FOR IDENTIFICATION

DATE 3/29/85 RPTD [Signature]

618 TALC BC*

Typical Chemical Analysis:

		Percent
Silica	SiO ₂	56-60
Calcium Oxide	CaO	0.4-1.2
Aluminum Oxide	Al ₂ O ₃	5-7.5
Magnesium Oxide	MgO	29-32
Ferric Oxide	Fe ₂ O ₃	0.2-0.6
Moisture	not more than	0.6
Loss on Ignition	not more than	10
Water Solubles	not more than	0.1
Acid Solubles	not more than	6
Water Soluble Iron		None
pH		8.8-9.8

Typical Physical Properties:

Dry Brightness	78-84
Specific Gravity	2.69
Tapped Density, lbs./cu.ft.	62-69
Loose Density, lbs./cu.ft.	24-30
Lbs./solid gallon	22.41
One Lb. Bulks, gallons	0.04462
Oil Absorption	22-28
Thru 200 Mesh, %	99
Thru 325 Mesh, %	93
Slip	Excellent

*Bacteria Controlled, CTFA, "Microbiological Limit Guidelines for Cosmetics and Toiletries, 1985." Combined count of less than 500 microorganisms per gram and the absence of gram negative bacteria.

PLAINTIFF'S
EXHIBIT
WCD-296

Issued: 1/84
Supersedes: E85