

GOODS: Alkyd House Paint - Tint Base

LABORATORY NO.

CONSISTENCY

COST CLASS.

DATE 6/10/60

FOR USE ONLY in Y-1856, Y-1857, Y-1859, Y-1886, Y-1887

STRAINER

GRIND 6

CUSTOMER TORONTO + SAN FRANCISCO Y-1888

MILL Pebble

WT. OR BE 9.5#

CODE NUMBER	ONE GALLON BATCH			ONLY LARGE BATCH			IS AGITATOR REQUIRED	
	PINTS	LBS.	OZS.	GALS.	LBS.	OZS.	VISC. F.B.	78-82 KU TEMP.
W-170 or W-208				(4.15)	145		VISC. RED.	TEMP.
W-188				(2.31)	55		VISCOSIMETER	Stormer
W-154				(2.44)	55		COLOR	SHEEN H1-Gloss
CH-185				(.26)	2.3		NON VOL.	FLASH PT.
W-218	Premix before			(.4)	6		MATCH FOR	
S-72	Adding to mill			.46	(3)		REDUCER	S-43
V-869				62.7	(492)		AMT. FOR BRUSHING	P.B.
O-265				14.0	(108)		SPRAYING	TUNBLING
S-43	Standard Formula.			9.5	(62)		DIPPING	DRIP TIME
VM-523	Not to be taken from File.			.5	(4)		BAKE	TEMP.
VM-433				.25	(2)		AIR DRIES IN	O.N.
VM-432				.63	(6)		A. O. TO RECOAT IN	48 hrs.
D-83				.58	(4)		REMARKS:	
CH-359				.70	(1.5)		CAUTION: WHEN DETERMININ VISCOSITY-MATERIAL IS THIXOTROPIC.	
VM-659				.8	(6.4)			
*Jelomer	903(M-486)			.28	(2.0)		FORMULATOR	J.E. Southwick
*Alkydol Labs. Inc.								
YIELD				99.4	954.2			

N12068

G D059040

